Green biosynthesis of silver nanoparticles using *Curcuma longa* tuber powder

Kamyar Shameli^{1,2}

Mansor Bin Ahmad¹

Ali Zamanian²

Parvanh Sangpour²

Parvaneh Shabanzadeh³

Yadollah Abdollahi⁴

Mohsen Zargar⁵

¹Department of Chemistry, Universiti Putra Malaysia, Serdang, Selangor, Malaysia; ²Materials and Energy Research Center, Karaj, Iran; ³Department of Mathematics, ⁴Advanced Materials and Nanotechnology Laboratory, Universiti Putra Malaysia, Serdang, Selangor, Malaysia; ⁵Department of Biology, Islamic Azad University, Qom, Iran

Abstract: Green synthesis of noble metal nanoparticles is a vastly developing area of research. Metallic nanoparticles have received great attention from chemists, physicists, biologists, and engineers who wish to use them for the development of a new-generation of nanodevices. In this study, silver nanoparticles were biosynthesized from aqueous silver nitrate through a simple and eco-friendly route using *Curcuma longa* tuber-powder extracts, which acted as a reductant and stabilizer simultaneously. Characterizations of nanoparticles were done using different methods, which included ultraviolet-visible spectroscopy, powder X-ray diffraction, transmission electron microscopy, scanning electron microscopy, energy-dispersive X-ray fluorescence spectrometry, and Fourier-transform infrared spectroscopy. The ultraviolet-visible spectrum of the aqueous medium containing silver nanoparticles showed an absorption peak at around 415 nm. Transmission electron microscopy showed that mean diameter and standard deviation for the formation of silver nanoparticles was 6.30 ± 2.64 nm. Powder X-ray diffraction showed that the particles are crystalline in nature, with a face-centered cubic structure. The most needed outcome of this work will be the development of value-added products from *C. longa* for biomedical and nanotechnology-based industries.

Keywords: silver nanoparticles, *Curcuma longa*, biosynthesis, green synthesis, transmission electron microscopy

Introduction

Green nanotechnology is an area with significant focus at present on the important objective of facilitating the manufacture of nanotechnology-based products that are eco-friendly and safer for all beings, with sustainable commercial viability. The “green synthesis” of metal nanoparticles receives great attention due to their unusual optical, chemical, photochemical, and electronic properties.¹ Metal nanoparticles, especially the noble metals, have mainly been studied because of their strong optical absorption in the visible region caused by the collective excitation of free-electron gas.²

Among noble metal nanoparticles, silver nanoparticles (Ag-NPs) have a wide area of interest, as they have a large number of applications, such as in nonlinear optics, spectrally selective coating for solar energy absorption, biolabeling, intercalation materials for electrical batteries as optical receptors, catalyst in chemical reactions, and as antibacterial capacities.

Ag-NPs have particular properties that may perhaps have numerous applications in the fields of dentistry, clothing, catalysis, mirrors, optics, photography, electronics, and the food industry.³ Because of such a broad variety of applications, many different preparation methods have been developed. However, the methods developed for Ag-NP

Correspondence: Kamyar Shameli
Department of Chemistry, Faculty
of Science, Universiti Putra Malaysia,
Serdang UPM 43400, Selangor, Malaysia
Tel +60 173 443 492
Fax +60 389 466 043
Email kamyarsameli@gmail.com

preparation must give preference to controlled size of Ag-NPs. Therefore, nanosilver with small particle size and devoid of aggregation between particles is favorable.

There are several ways to reduce Ag^+ , eg, use of γ -rays,⁴ ultraviolet (UV) irradiation,⁵ heating and electrochemical reduction,⁶ and application of reducing chemicals, such as hydrazine,⁷ sodium borohydride,^{8–10} polyethylene glycerol,¹¹ *N,N*-dimethylformamide,¹² glucose,¹³ ethylene glycol,¹⁴ formaldehyde,¹⁵ and sodium in liquid ammonia.¹⁶ However, there is still need for a more economic, commercially viable, and environmentally green synthesis route to synthesize Ag-NPs. The green synthesis of Ag-NPs involves three main steps, which must be evaluated based on green chemistry perspectives, including selection of solvent medium, reducing agent, and nontoxic stabilizers for Ag-NPs.¹⁷

The biosynthesis of nanoparticles, which represents a connection between biotechnology and nanotechnology, has received increasing consideration due to the growing need to develop environmentally friendly technologies for material syntheses. The search for appropriate biomaterials for the biosynthesis of nanoparticles continues through many different synthetic methods.¹⁸

The biosynthetic method using plant extracts has received more attention than chemical and physical methods and even the use of microbes. The method is suitable for nanoscale metal synthesis due to the absence of any requirement to maintain an aseptic environment.¹⁹ The possibility of using plant materials for the synthesis of nanoscale metals was reported initially by Gardea-Torresdey et al.^{20,21} Later, the bioreduction of various metals to nanosize materials of various shapes, capable of meeting the requirements of diverse industrial applications, was extensively studied.²² In continuation, we have demonstrated the prospect of using *Vitex negundo* L leaf and *Callicarpa manigayi* stem-bark methanolic extracts for the synthesis of Ag-NPs in ambient conditions, without any additive protecting nanoparticles from aggregating, template shaping nanoparticles or accelerants.^{23,24}

In this study, the synthesis and characterization of Ag/*Curcuma longa* by a green method is reported. The Ag-NPs were prepared using silver nitrate as silver precursor and *C. longa* tuber-powder water extract as reducing agent and stabilizer.

Materials and methods

Materials

The *C. longa* tubers were purchased from a local market in Malaysia. AgNO_3 (99.98%) was used as a silver precursor, and was provided by Merck (Darmstadt, Germany). HNO_3 (70%) and HCl (37%) were obtained from Sigma-Aldrich (St Louis, MO). All reagents in this effort were analytical grade and were used as received without further purification. All solutions were freshly prepared using double-distilled water and kept in the dark to avoid any photochemical reactions. All glassware used in experimental procedures was cleaned in a fresh solution of HNO_3/HCl (3:1, v/v), washed thoroughly with double-distilled water, and dried before use.

Extraction preparation

The *C. longa* plant and tubers are shown in Figure 1A and B. The *C. longa* tubers were washed to remove the adhering mud particles and possible impurities. Later they were dried under sunlight for a week to completely remove the moisture. The tubers were cut into small pieces, powdered in a mixer, and then sieved using a 20-mesh sieve to get uniform size range. The final sieved powder was used for all further studies (Figure 1C). For the production of extract, 0.1 g of *C. longa* tuber powder was added to a 100 mL Erlenmeyer flask with 20 mL sterile distilled water and then mixed for 4 hours at room temperature.

Synthesis of Ag/*C. longa* emulsion

Briefly, water extract of *C. longa* tubers (0.1 g) was added to distilled deionized water (20 mL) with vigorous

Figure 1 *Curcuma longa* plant (A), *C. longa* tubers (B), and *C. longa* powder (C).

stirring for 4 hours. Forty milliliters of AgNO_3 (1×10^{-3} M) was then added and mixed at room temperature (25°C) for 24 hours. Ag-NPs were gradually obtained during the incubation period. Throughout the reduction process, the solution was kept at a room temperature in the dark to avoid any photochemical reactions. The solution component was purged with nitrogen gas prior to use. Subsequently, reduction proceeded in the presence of nitrogen to eliminate oxygen. The obtained colloidal suspensions of Ag/C. longa were then centrifuged at 15,000 rpm for 20 minutes and washed four times to remove silver ion residue. The precipitate nanoparticles were then dried overnight at 30°C under vacuum to obtain the Ag/C. longa.

Characterization methods and instruments

The prepared Ag/C. longa were characterized by UV-visible spectroscopy, X-ray diffraction (XRD), transmission electron microscopy (TEM), scanning electron microscopy (SEM), energy dispersive X-ray fluorescence spectrometry (EDXRF) and Fourier-transform infrared (FT-IR) spectroscopy. The UV-visible spectra were recorded over the 300–800 nm range with a UV-1650 PC UV-visible spectrophotometer (Shimadzu, Osaka, Japan). The structures of the Ag-NPs produced were examined by XRD (XRD-6000; Shimadzu). The XRD patterns were recorded at a scan speed of $4^\circ/\text{minute}$. TEM observations were carried out on a H-7100 electron microscope (Hitachi, Tokyo, Japan), and the particle-size distributions were determined using the UTHSCSA Image Tool version 3.00 program (freeware). SEM was performed using a Philips XL-30 instrument (Philips, Eindhoven, Netherlands) to study the morphology of Ag/C. longa. The EDXRF was carried out on a DX-700HS spectrometer (Shimadzu). Meanwhile, the FT-IR spectra were recorded over the range of $400\text{--}4000\text{ cm}^{-1}$ using an FT-IR Series 100, 1650 PerkinElmer spectrophotometer (Los Angeles, CA).

Results and discussion

The reduction of Ag^+ into Ag-NPs during exposure to water extract of C. longa tuber powder was able to be followed by the color change. The fresh suspension of C. longa was yellow. However, after the addition of AgNO_3 and stirring for 24 hours at room temperature, the emulsion turned brown.

The color changes in aqueous solutions are due to the surface-plasmon resonance (SPR) phenomenon (Figure 2A and B). The result obtained in this investigation is interesting because it can serve as a foundation in terms of identification of potential forest plants for synthesizing Ag-NPs.

Figure 2 Photograph of *Curcuma longa* (A) and silver/*C. longa* (B) emulsions after 24 hours of stirring time.

C. longa as an aldehyde can reduce silver ions to Ag-NPs. The possible chemical equations for preparing the Ag-NPs are:

After dispersion of silver ions in the C. longa aqueous solution matrix (Equation 1), the extract was reacted with the $\text{Ag}^+_{(\text{aq})}$ to form $[\text{Ag (C. longa)}]^+$ complex, which reacted with aldehyde groups in the molecular structure of the methanolic extract to form $[\text{Ag (C. longa)}]$, due to the reduction of silver ions through the oxidation of aldehyde to carboxylic acid groups (Equation 2).

UV-visible spectroscopy analysis

The formation of Ag-NPs was followed by measuring the SPR of the C. longa and Ag/C. longa emulsions over the wavelength range of 300–800 nm (Figure 3B). The SPR bands are influenced by the size, shape, morphology, composition, and dielectric environment of the prepared nanoparticles.^{25,26} Previous studies have shown that the spherical Ag-NPs contribute to the absorption bands at around 400–420 nm in the UV-visible spectra.^{26,27} These absorption bands were assumed to correspond to the Ag-NPs' extra-fine nature, with relatively small size. UV-visible absorption spectra (Figure 3B) showed that the broad SPR band contained one peak at 415 nm. This peak illustrates the presence of a homogeneous distribution of hydrosol Ag-NPs after 24 hours stirring.^{11,23} For the stability test of the Ag-NP emulsion, the absorption spectrum of the sample was measured after storage for 3 months (Figure 3C). The absorption peak of the Ag-NPs shifted slightly from 415 to 417 nm, but the spectra for these two samples showed significant changes in either peak intensity or spectral shape.²⁷ Thus, with the comparison of Figure 3B and C, it can be

Figure 3 UV-visible absorption spectra of *Curcuma longa* (A) and silver (Ag)/*C. longa* emulsion (B) after 24 hours of stirring; Ag/*C. longa* emulsion (C) after 3 months.

concluded that for emulsion stability testing, due to the decreases in absorbance intensity and deposits of Ag-NPs, at first the stability of the Ag/*C. longa* emulsion decreases and then gradually the size of the Ag-NPs increases.

Powder X-ray diffraction

Figure 4 shows the XRD patterns of vacuum-dried Ag-NPs synthesized using *C. longa*. The XRD patterns of Ag/*C. longa* indicated that the structure of Ag-NPs is

face-centered cubic.²⁷ In addition, all the Ag-NPs had a similar diffraction profile, and XRD peaks at 2θ of 38.18° , 44.25° , 64.72° , and 77.40° could be attributed to the 111, 200, 220, and 311 crystallographic planes of the face-centered cubic silver crystals, respectively.²⁸ The XRD pattern thus clearly illustrated that the Ag-NPs formed in this study were crystalline in nature. The main crystalline phase was silver, and there were no obvious other phases as impurities were found in the XRD patterns (Figure 4).

Figure 4 X-ray diffraction patterns of silver nanoparticles (Ag-NPs) synthesized in *Curcuma longa* for determination of Ag-NPs after 24 hours of stirring. Abbreviation: XRD, X-ray diffraction.

The average particle size of Ag-NPs can be calculated using the Debye–Scherrer equation (3):

$$n = \frac{K\lambda}{\beta \cos \theta} \quad (3)$$

where K is the Scherrer constant with value from 0.9 to 1 (shape factor), where λ is the X-ray wavelength (1.5418 Å), $\beta_{1/2}$ is the width of the XRD peak at half-height and θ is the Bragg angle. From the Scherrer equation, the average crystallite size of Ag-NPs for the sample at 24 hours of stirring are found to be lower than 10 nm in size, which is also in line with the TEM results discussed later.

Morphology study

For TEM, a drop of the Ag-NP solution synthesized by treating silver nitrate solution with *C. longa* was deposited onto a TEM copper grid. After drying, the grid was imaged using TEM. The TEM images and their size distribution are shown in Figure 5A and B; the result showed narrow particle-size distributions, with diameters in the range of 3.66–8.94 nm. Moreover, the mean diameter and standard deviation of Ag-NPs was 6.30 ± 2.64 nm.

The presence of one narrow distribution of Ag-NPs in the TEM images is in accordance with the UV-visible

spectral study. Figure 5C and D show the Ag-NPs surrounded by the extract of *C. longa*. The dark points in this figure represent the large-scale distribution of Ag-NPs. The Ag-NPs surrounded by *C. longa* extract is shown by TEM in Figure 5 and confirmed by FT-IR spectroscopy. The number of Ag-NPs counted for TEM imaging was around 483 at 24 hours stirring. Figure 6A–D shows the SEM images and EDXRF spectra for the *C. longa* and Ag/*C. longa* emulsion after 24 hours stirring. These results confirm that extract of *C. longa* can effectively control the shape and size of the Ag-NPs.

The exterior surfaces of Ag/*C. longa* due to the presence of small Ag-NPs become shiny in the spots' spherical shapes (Figure 6C). Figure 6B shows the EDXRF spectra for the *C. longa*; the peaks around 1.7, 2.8, 3.8, and 4.5 keV are related to the binding energies of *C. longa*. In Figure 6D, the peaks around 1.3, 3.1, 3.3, and 3.4 keV are related to the silver elements in the *C. longa*.²⁹

Additionally, the EDXRF spectra for the Ag/*C. longa* confirmed the presence of Ag-NPs in the tuber-powder extraction without any impurity peaks. From EDXRF spectra, it is clear that *C. longa* has a yield of 45.53% of Ag-NPs. The results indicate that the synthesized nanoparticles are composed of high-purity Ag-NPs.

Figure 5 (A–D) Transmission electron microscopy images and corresponding size distribution of silver/*Circuma longa* after 24 hours of stirring.
Abbreviations: Std Dev, standard deviation; Ag-NPs, silver nanoparticles.

Figure 6 Scanning electron microscopy image and energy-dispersive X-ray fluorescence spectrometry spectra of *Curcuma longa* (A and B) and silver/*C. longa* (C and D) formation after 24 hours of stirring.

Abbreviation: Ag-NPs, silver nanoparticles.

FT-IR chemical analysis

The FT-IR spectra were recorded to identify the possible biomolecules responsible for the reduction of the Ag^+ ions and capping of the bioreduced Ag-NPs synthesized by the *C. longa* extract. After complete bioreduction of Ag^+ , the *C. longa* tuber-powder extract was centrifuged at 15,000 rpm for 20 minutes to isolate the Ag-NPs from proteins and other compounds present in the solution. Figure 7A shows the FT-IR spectrum of *C. longa* tuber powder that did not contain AgNO_3 , whereas Figure 7B shows the spectrum containing

Ag-NPs after extract bioreduction with AgNO_3 . The spectrum in Figure 7A shows transmission peaks at 3295, 2923, 1638, 1375, 1134, 1004, 851, 514, and 393 cm^{-1} . Similarly, transmission peaks for the tuber-powder extract containing Ag-NPs were at 3329, 2920, 1952, 1643, 1420, 1147, 1011, 867, 689, 510, and 299 cm^{-1} . Three absorption peaks located around 867, 1011 and 1147 cm^{-1} can be assigned as the absorption peaks of $-\text{C}-\text{N}$ stretching vibrations of the amine, $-\text{C}-\text{O}-\text{C}$ or $-\text{C}-\text{O}$ groups, respectively.^{24,30} The bonds or functional groups such as $-\text{C}-\text{O}-\text{C}-$, $-\text{C}-\text{O}$, and

Figure 7 Fourier-transform infrared spectra for the *Curcuma longa* tuber-powder extract (A) and Ag/*C. longa* (B) after 24 hours from biosynthesis reaction.

—C=C— derived from heterocyclic compounds, eg, alkaloid or flavones, and the amide (I) bond derived from the proteins that are present in the tuber-powder extract are the capping ligands of the nanoparticles.³¹ The broad and strong bands at 3329–2920 cm⁻¹ were due to bonded hydroxyl (—OH) or amine groups (—NH) and aliphatic C—H of the *C. longa* tuber-powder extract, respectively. The peak at 1643 cm⁻¹ is attributed to the carboxyl group (—C=O) stretching vibration. The adsorption at around 1375–1420 cm⁻¹ notably showed that —NO₃ existed in residual amounts.²⁴ The broad peaks at 510 and 299 cm⁻¹ and also the peak in 1952 cm⁻¹ are related to Ag-NP banding with oxygen from hydroxyl groups of *C. longa* compounds (Figure 7B).²⁷

Conclusion

Ag-NPs with an average size of 6.30 ± 2.64 nm and spherical shapes were synthesized using aqueous tuber-powder extract of *C. longa*. The Ag-NPs were characterized by UV-visible, XRD, TEM, SEM, EDXRF, and FT-IR spectra. Biosynthesis of Ag-NPs using green resources like *C. longa* is a better alternative to chemical synthesis, since this green synthesis is pollutant-free and eco-friendly. From the results obtained in this research, one can affirm that *C. longa* tuber powder can play an important role in the bioreduction and stabilization of silver ions to Ag-NPs.

Acknowledgments

The authors thank the University Putra Malaysia (UPM) for its financial support (RUGS, Project no 9199840). The authors are also grateful to the staff of the Department of Chemistry, UPM, for their help in this research, and the Institute of Bioscience (IBS/UPM) for technical assistance.

Disclosure

The authors report no conflicts of interest in this work.

References

- Mohanpuria P, Rana NK, Yadav SK. Biosynthesis of nanoparticles: technological concepts and future applications. *J Nanopart Res*. 2008;10:507–517.
- Mohamed MB, Volkov V, Link S, Sayed MAE. The ‘lightning’ gold nanorods: fluorescence enhancement of over a million compared to the gold metal. *Chem Phys Lett*. 2000;317:517–523.
- Rai M, Yadav A, Gade A. Silver nanoparticles as a new generation of antimicrobials. *Biotechnol Adv*. 2009;27:76–83.
- Shameli K, Ahmad MB, Wan Yunus WMZ, Ibrahim NA, Gharayebi Y, Sedaghat S. Synthesis of silver/montmorillonite nanocomposites using γ -irradiation. *Int J Nanomedicine*. 2010;5:1067–1077.
- Shameli K, Ahmad MB, Wan Yunus WMZ, et al. Green synthesis of silver/montmorillonite/chitosan bionanocomposites using the UV-irradiation method and evaluation of antibacterial activity. *Int J Nanomedicine*. 2010;5:875–887.
- Zhang Y, Chen F, Zhuang J, et al. Synthesis of silver nanoparticles via electrochemical reduction on compact zeolite film modified electrodes. *Chem Commun (Camb)*. 2002;2814–2815.
- Szczepanowicz K, Stefańska J, Socha RP. Preparation of silver nanoparticles via chemical reduction and their antimicrobial activity. *Physicochem Probl Miner Process*. 2010;45:85–98.
- Shameli K, Ahmad MB, Zargar M, Wan Yunus WMZ, Rustaiyan A, Ibrahim NA. Synthesis of silver nanoparticles in montmorillonite and their antibacterial behavior. *Int J Nanomedicine*. 2010;6:581–590.
- Shameli K, Ahmad MB, Wan Yunus WMZ, Ibrahim NA. Synthesis and characterization of silver/talc nanocomposites using the wet chemical reduction method. *Int J Nanomedicine*. 2010;5:743–751.
- Shameli K, Ahmad MB, Zargar M, Wan Yunus WMZ, Ibrahim NA. Fabrication of silver nanoparticles doped in the zeolite framework and antibacterial activity. *Int J Nanomedicine*. 2011;6:331–341.
- Shameli K, Ahmad MB, Jazayeri SD, et al. Synthesis and characterization of polyethylene glycol mediated silver nanoparticles by the green method. *Int J Mol Sci*. 2012;13:6639–6650.
- Pastoriza-Santos I, Liz-Marzán LM. Formation and stabilization of silver nanoparticles through reduction by N,N-dimethylformamide. *Langmuir*. 1999;15:948–951.
- Ahmad MB, Shameli K, Wan Yunus WMZ, Ibrahim NA. Synthesis and characterization of silver/clay/starch bionanocomposites by green method. *Aust J Basic Appl Sci*. 2010;4:2158–2165.
- Setua P, Pramanik R, Sarkar S. Synthesis of silver nanoparticle inside the nonaqueous ethylene glycol reverse micelle and a comparative study to show the effect of the nanoparticle on the reverse micellar aggregates through solvation dynamics and rotational relaxation measurements. *J Phys Chem B*. 2010;114:7557–7564.
- Praus P, Turicová M, Klementová M. Preparation of silver-montmorillonite nanocomposites by reduction with formaldehyde and borohydride. *J Braz Chem Soc*. 2009;20:1351–1357.
- Sun L, Zhang Z, Dang H. A novel method for preparation of silver nanoparticles. *Mater Lett*. 2003;57:3874–3879.
- Raveendran P, Fu J, Wallen SL. Completely “green” synthesis and stabilization of metal nanoparticles. *J Am Chem Soc*. 2003;125:13940–13941.
- Sathishkumar M, Sneha K, Won SW, Cho CW, Kim S, Yun YS. *Cinnamomum zeylanicum* bark extract and powder mediated green synthesis of nano-crystalline silver particles and its bactericidal activity. *Colloid Surface B*. 2009;73:332–338.
- Rai A, Singh A, Ahmad A, Sastry M. Role of halide ions and temperature on the morphology of biologically synthesized gold nanotriangles. *Langmuir*. 2006;22:736–741.
- Gardea-Torresdey JL, Parsons JG, Dokken K, et al. Formation and growth of Au nanoparticles inside live alfalfa plants. *Nano Lett*. 2002;2:397–401.
- Gardea-Torresdey JL, Gomez E, Peralta-Videa JR, Parsons JG, Troiani H, Jose-Yacamán M. Alfalfa sprouts: a natural source for the synthesis of silver nanoparticles. *Langmuir*. 2003;19:1357–1361.
- Shankar SS, Rai A, Ankamwar B, Singh A, Ahmad A, Sastry M. Biological synthesis of triangular gold nanoprisms. *Nat Mater*. 2004;3:482–488.
- Zargar M, Hamid AA, Bakar FA, et al. Green synthesis and antibacterial effect of silver nanoparticles using *Vitex negundo* L. *Molecules*. 2011;16:6667–6676.
- Shameli K, Ahmad MB, Al-Mulla EAJ, et al. Green biosynthesis of silver nanoparticles using *Callicarpa maingayi* stem bark extraction. *Molecules*. 2012;17:8506–8517.
- Kelly KL, Coronado E, Zhao LL, Schatz GC. The optical properties of metal nanoparticles: the influence of size, shape and dielectric environment. *J Phys Chem B*. 2003;107:668–677.
- Stepanov AL. Optical properties of metal nanoparticles synthesized in a polymer by ion implantation: a review. *Tech Phys*. 1997;49:143–153.

27. Shameli K, Ahmad MB, Jazayeri SD, et al. Investigation of antibacterial properties silver nanoparticles prepared via green method. *Chem Cent J*. 2012;6:73.
28. Ahmad MB, Shameli K, Darroudi M, Wan Yunus WMZ, Ibrahim NA. Synthesis and characterization of silver/clay nanocomposites by chemical reduction method. *Am J Appl Sci*. 2009;6:1909–1914.
29. Shameli K, Ahmad MB, Zargar M, et al. Synthesis and characterization of silver/montmorillonite/chitosan bionanocomposites by chemical reduction method and their antibacterial activity. *Int J Nanomedicine*. 2011;6:271–284.
30. Huang J, Li Q, Sun D, et al. Biosynthesis of silver and gold nanoparticles by novel sundried *Cinnamomum camphora* leaf. *Nanotechnology*. 2007;18:1–11.
31. Luo L, Yu S, Qian S, Zhou T. Large-scale fabrication of flexible silver/cross-linked poly(vinyl alcohol) coaxial nanoscale by a facial solution approach. *J Am Chem Soc*. 2005;127:2822–2823.

International Journal of Nanomedicine

Publish your work in this journal

The International Journal of Nanomedicine is an international, peer-reviewed journal focusing on the application of nanotechnology in diagnostics, therapeutics, and drug delivery systems throughout the biomedical field. This journal is indexed on PubMed Central, MedLine, CAS, SciSearch®, Current Contents®/Clinical Medicine,

Submit your manuscript here: <http://www.dovepress.com/international-journal-of-nanomedicine-journal>

Dovepress

Journal Citation Reports/Science Edition, EMBase, Scopus and the Elsevier Bibliographic databases. The manuscript management system is completely online and includes a very quick and fair peer-review system, which is all easy to use. Visit <http://www.dovepress.com/testimonials.php> to read real quotes from published authors.