Curcumin Ag nanoconjugates for improved therapeutic effects in cancer

Darshini Shah
Reema Savaliya
Pal Patel
Krupa Kansara
Alok Pandya
Alok Dhawan
Sanjay Singh

Institute of Life Sciences, School of
Science and Technology, Ahmedabad
University, Ahmedabad, Gujarat, India

Abstract: Curcumin has a broad spectrum of pharmacological activities, one of them is anticancer activity that is mediated through multiple mechanisms. The major disadvantage associated with the use of curcumin is its low bioavailability due to its poor aqueous solubility. Nanoformulations of curcumin provide an effective solution for this problem. In this study, we have synthesized curcumin Ag nanoconjugates and evaluated their anticancer potential.

Keywords: curcumin, anticancer, nanoconjugate, AgNPs

Introduction

The major challenge faced by modern scientific and medical research is the need to develop new anticancer treatments with greater efficacy and fewer side effects.¹ Natural products have been widely used by our ancestors to combat illness, and that trend has been growing over the past few decades. Current medicines have been revolutionary in curing diseases, but their harmful side effects have led to the use of natural products. Curcumin is one of the many natural products containing such beneficiary properties. Curcumin is a polyphenol derived from *Curcuma longa* plant, commonly known as turmeric. Curcumin has been used extensively in Ayurvedic medicine for centuries, as it is nontoxic and has a variety of therapeutic properties including antioxidant, analgesic, anti-inflammatory, and antiseptic activities.² Recently, curcumin has been shown to possess anticancer activities through its effect on a variety of biological pathways. It has not been clinically used yet, due to its sparing solubility in water and low bioavailability. Various studies have reported that the bioavailability of curcumin could be increased by conjugating it with metal nanoparticles (NPs). Hence, in this study, we have made an attempt to synthesize AgNPs functionalized by curcumin and analyze its anticancer properties. The effects of curcumin-reduced AgNPs (C-AgNPs), L-tyrosine-reduced AgNPs (T-AgNPs), and free curcumin on the viability of human epidermoid carcinoma cell line (A431 cells) was compared.

Materials and methods

Curcumin AgNPs synthesis

C-AgNPs were synthesized using the method described by Bettini et al with slight modifications.³ Briefly, AgNO_3 (10^{-3} M) was mixed with 10^{-5} M curcumin solution. The pH was adjusted to 9 using 1 M NaOH, and the solution was allowed to boil until the color changed to orangish yellow.

Synthesis of T-AgNPs

T-AgNPs were synthesized using the method described by Selvakannan et al with slight modifications.⁴ Briefly, AgNO_3 (10^{-3} M) solution was mixed with 10^{-3} M aqueous

Correspondence: Sanjay Singh
Institute of Life Sciences, School
of Science and Technology, Ahmedabad
University, Navrangpura, Ahmedabad,
Gujarat 380009, India
Email sanjay.singh@ahduni.edu.in

solution of L-tyrosine in 1:1 ratio. The pH was adjusted to 10 using 1 M NaOH, and this solution was allowed to boil until the color changed to yellow.

Characterization of AgNPs

C-AgNPs and T-AgNPs were dialyzed for 24 h by 12 kDa dialysis bag against the copious amount of deionized water. This removed the unreduced ions of Ag and other reaction products, which might have formed during the NPs synthesis. Dialysis also decreased the pH (~7) of NPs suspension, which was alkaline (>9) as required by NPs synthesis. Hydrodynamic size and zeta potential of C-AgNPs and T-AgNPs were determined using Zetasizer Nano-ZS, and absorbance spectrum was determined using UV–visible spectrophotometer (Synergy HT multi-mode microplate reader).

Cell viability assessment

The effects of curcumin, C-AgNPs, and T-AgNPs was determined using 3-(4,5-dimethylthiazol-2-yl)-2,5 diphenyltetrazolium bromide (MTT) assay on A431 cell line.⁵ A431 cells were commercially purchased from the National Center for Cell Sciences, Pune, India.

Results and discussion

The hydrodynamic size and zeta potential of C-AgNPs and T-AgNPs were found to be 29.0 ± 0.10 , -27 ± 2.30 and 41.72 ± 0.21 , -30.0 ± 0.66 , respectively (Table 1). The synthesized AgNP solutions were stable for more than a month. High zeta potential value further supports the high stability of AgNP solutions.

The UV–visible absorbance (Figure 1) spectrum of C-AgNPs and T-AgNPs along with their respective controls was recorded as shown in Figure 1. The maximum absorbance of C-AgNPs was found to be 420 nm, and it coincides with that of T-AgNPs, indicating that AgNPs have been successfully synthesized. Other solutions such as curcumin, AgNO_3 -NaOH, curcumin- AgNO_3 , and curcumin-NaOH after extensive boiling showed absorbance

Figure 1 UV–visible spectrum of C-AgNPs and T-AgNPs along with controls. **Abbreviations:** C-AgNPs, curcumin-reduced AgNPs; T-AgNPs, L-tyrosine-reduced AgNPs.

at 425 nm, 530 nm, 425 nm, and 460 nm. However, as clearly evident in Figure 1, the absorbance intensity of these solutions was found to be very weak and did not match with the absorbance of AgNPs.

Human skin carcinoma cells (A431) were exposed to different concentrations of free curcumin, T-AgNPs, and C-AgNPs for 24 h, and cell viability was determined using MTT assay. Here, curcumin concentration corresponds to the amount of curcumin required to synthesize 40 and 60 $\mu\text{g/mL}$ of C-AgNPs (Figure 2). Free curcumin showed only marginal decrease in cell viability. However, T-AgNPs showed a concentration-dependent decrease in cell viability ranging

Figure 2 Cell viability assessment of curcumin, T-AgNPs, and C-AgNPs on A431 cells. **Abbreviations:** C-AgNPs, curcumin-reduced AgNPs; T-AgNPs, L-tyrosine-reduced AgNPs.

Table 1 Hydrodynamic size and zeta potential of C-AgNPs and T-AgNPs

Characteristics	Nanoparticles	
	C-AgNPs	T-AgNPs
Hydrodynamic size (d. nm)	29.0 ± 0.10	41.72 ± 0.21
Zeta potential (mV)	-27.7 ± 2.30	-30.0 ± 0.66
PDI	0.25 ± 0.002	0.22 ± 0.009

Note: Data presented as mean $\pm$ SD.

Abbreviations: C-AgNPs, curcumin-reduced AgNPs; PDI, polydispersity index; T-AgNPs, L-tyrosine-reduced AgNPs.

from 20% (at 40 $\mu\text{g/mL}$) to 37% (at 60 $\mu\text{g/mL}$). However, exposure to C-AgNPs leads to significant reduction in cell viability ranging from 44% to 98.5% at 40 and 60 $\mu\text{g/mL}$ concentrations, respectively (Figure 2). This observation suggests that the synergistic anticancer effect of curcumin and AgNPs leads to cell death in A431 cells.

Conclusion

C-AgNPs and T-AgNPs are found to be toxic to the skin carcinoma (A431) cells than free curcumin at higher concentration (60 $\mu\text{g/mL}$). Promising anticancer activity of C-AgNPs suggests its potential to be used as a chemotherapeutic agent for cancer treatment.

Acknowledgments

The authors gratefully acknowledge the Centre for Nanotechnology Research and Applications (CENTRA) by The Gujarat Institute for Chemical Technology (GICT). RS would like to thank the University Grant Commission (UGC),

New Delhi, for the award of Junior Research Fellowship. The manuscript contains ILS-manuscript No 045.

Disclosure

The authors report no conflicts of interest in this work.

References

1. Salem M, Rohani S, Gillies ER. Curcumin, a promising anti-cancer therapeutic: a review of its chemical properties, bioactivity and approaches to cancer cell delivery. *RSC Advances*. 2014;4(21):10815–10829.
2. Wilken R, Veena MS, Wang MB, Srivatsan ES. Curcumin: a review of anti-cancer properties and therapeutic activity in head and neck squamous cell carcinoma. *Mol Cancer*. 2011;10(12):1–19.
3. Bettini S, Pagano R, Valli L, Giancane G. Drastic nickel ion removal from aqueous solution by curcumin-capped Ag nanoparticles. *Nanoscale*. 2014;6(17):101–113.
4. Selvakannan PR, Swami A, Srisathiyarayanan D, et al. Synthesis of aqueous Au core-Ag shell nanoparticles using tyrosine as a pH-dependent reducing agent and assembling phase-transferred silver nanoparticles at the air-water interface. *Langmuir*. 2004;20(18):7825–7836.
5. Mosmann T. Rapid colorimetric assay for cellular growth and survival: application to proliferate and cytotoxicity assays. *J Immunol Methods*. 1983;65(1–2):55–63.

International Journal of Nanomedicine

Publish your work in this journal

The International Journal of Nanomedicine is an international, peer-reviewed journal focusing on the application of nanotechnology in diagnostics, therapeutics, and drug delivery systems throughout the biomedical field. This journal is indexed on PubMed Central, MedLine, CAS, SciSearch®, Current Contents®/Clinical Medicine,

Submit your manuscript here: <http://www.dovepress.com/international-journal-of-nanomedicine-journal>

Dovepress

Journal Citation Reports/Science Edition, EMBase, Scopus and the Elsevier Bibliographic databases. The manuscript management system is completely online and includes a very quick and fair peer-review system, which is all easy to use. Visit <http://www.dovepress.com/testimonials.php> to read real quotes from published authors.