Potential Applications of Nanomaterials and Technology for Diabetic Wound Healing

This article was published in the following Dove Press journal:
International Journal of Nanomedicine

Que Bai^{1,*}
Kai Han^{1,*}
Kai Dong¹
Caiyun Zheng¹
Yanni Zhang¹
Qianfa Long²
Tingli Lu¹

¹School of Life Sciences, Northwestern Polytechnical University, Xi'an, Shaanxi 710072, People's Republic of China;

²Mini-Invasive Neurosurgery and Translational Medical Center, Xi'an Central Hospital, Xi'an Jiaotong University, Xi'an 710003, People's Republic of China

*These authors contributed equally to this work

Abstract: Diabetic wound shows delayed and incomplete healing processes, which in turn exposes patients to an environment with a high risk of infection. This article has summarized current developments of nanoparticles/hydrogels and nanotechnology used for promoting the wound healing process in either diabetic animal models or patients with diabetes mellitus. These nanoparticles/hydrogels promote diabetic wound healing by loading bioactive molecules (such as growth factors, genes, proteins/peptides, stem cells/exosomes, etc.) and non-bioactive substances (metal ions, oxygen, nitric oxide, etc.). Among them, smart hydrogels (a very promising method for loading many types of bioactive components) are currently favored by researchers. In addition, nanoparticles/hydrogels can be combined with some technology (including PTT, LBL self-assembly technique and 3D-printing technology) to treat diabetic wound repair. By reviewing the recent literatures, we also proposed new strategies for improving multifunctional treatment of diabetic wounds in the future.

Keywords: hydrogels, nanoparticles, nanotechnology, diabetic wound healing

Introduction

Diabetes mellitus is a complex metabolic disorder that affects the health of millions of people around the world. The world of diabetes among adults (aged 20–79 years) are 285 million adults, which will increase to 439 million adults by 2030.^{1,2} Diabetics will lead to high glucose condition as well as a variety of complications, including cardiovascular disease, nerve damage (neuropathy), kidney damage (kidney disease), eye damage (retinopathy), hearing impairment, dementia, and especial the delayed wound healing which is one of the most serious complications of diabetes impaired wound healing.^{3–9} Severe diabetic wounds could lead to amputation.¹⁰ Diabetes can be divided into four main types: Type I diabetes is caused by the autoimmune be destroyed of β -cells in the pancreas, eventually leading to reduction of insulin production;^{11,12} Type II diabetes is closely associated with insulin resistance and subsequent decompensation of pancreatic β -cells (including pancreatic β -cell mass loss and β -cell dysfunction);¹³ Gestational diabetes occurs during pregnancy and causes glucose intolerance;¹⁴ other diabetes are resulted by specific genetic defects of beta-cell function, illness of the pancreas, drugs or chemicals, etc.¹⁵

Normal Wound Healing

Wound healing is a complex and ordered biological process, including four classical stages: hemostasis, inflammation, proliferation and remodeling,^{16–18} involving

Correspondence: Qianfa Long; Tingli Lu
Tel +86 029-88460332
Email lonva@live.cn;
lutinglixinxin@nwpu.edu.cn

different cell types releasing many cytokines and growth factors (GFs).^{19,20} Hemostasis lasts 2–3 hours, the fibrin plug is formed, and aggressive platelets release pro-inflammatory mediators such as cytokines and growth factors. Cytokines recruit neutrophils and monocytes to the wound area, triggering an inflammatory period of wound healing that lasts from hours to days.²¹ The inflammatory phase begins immediately after injury and can last from hours to days in acute wounds, while in chronic wounds it can last for weeks or even months due to the effects of the underlying disease (eg, diabetic foot ulcers).¹⁶ Injury results in the rupture of vessels, and form clots and temporary extracellular matrix (ECM), which closes the wound, reduces blood loss, and helps guide cell migration.²² Platelets secrete and activate cellular mediators that attract inflammatory cells (multinucleated cells and macrophages), fibroblasts, and endothelial cells.²³ In the proliferation, endothelial cell and fibroblast proliferation and migration promote angiogenesis and new ECM formation.¹⁶ As the new ECM is reconstructed, the old matrix is degraded by proteases (matrix metalloproteinases, MMPs), MMPs promote autolytic debridement and cell migration in wounds.^{16,17} The level of MMPs in wounds increases after tissue damage and decreases with remission of inflammation, but increases abnormally in chronic wounds.¹⁷ Epithelial cells migrate from the edge of the wound, initiating epithelialization.²⁴ Keratinocyte differentiation helps restore the barrier function of the epidermis.²⁵ Remodeling can last for months and eventually an eschar (scab) has formed on the surface of the wound.¹⁷ The matrix is constantly reconstructed by myofibroblasts.¹⁶ The microfilaments attached to the ECM densify the collagen network and contract the wound.²⁶ At the same time, new components are secreted to increase matrix density and stability.^{26,27} The proportion of different types of collagen began to change: the proportion of type I collagen increased (80%–90%) and the proportion of type III collagen decreased (10%–20%).²⁸ Apoptosis reduces the density of myofibroblasts, making room for fibroblasts, further strengthening the ECM, and increasing its resistance to mechanical forces.²⁶

Diabetic Wound Healing

Under normal physiological conditions, the injured tissue will initiate the acute wound healing process.^{16–18} However, when the healing process is disturbed by the underlying pathological mechanism or microbial invasion,

the wound cannot heal and become a chronic wound (such as diabetic wound)²⁹ (Figure 1). Hypoxia is a major cause of diabetic wound damage caused by two factors: limited oxygen supply and high oxygen consumption in the wound.³⁰ In diabetic patients, oxygen supply to the wound is limited due to vascular dysfunction and neuropathy.³⁰ In addition to inadequate oxygen supply, high oxygen consumption by wound cells during inflammation also induces hypoxia in wounds.³⁰ In diabetic patients, the imbalance between angiogenic factors (eg, transforming growth factor- β , TGF- β ; fibroblast growth factor 2, FGF2; vascular endothelial growth factor, VEGF; angiopoietins) and angiostatic factors (eg, thrombospondins, endostatin, angiostatin) may lead to angiogenic imbalance and aggravate wound hypoxia.³¹ Likewise, hypoxia can amplify the inflammatory response, thereby prolonging injury by increasing the levels of oxygen radicals.³² Two main events for effective wound healing involve an inflammatory response and migration of keratinocytes, fibroblasts, and endothelial cells. However, diabetic wounds did not undergo a normal healing process rather trapped into a chronic inflammatory stage characterized by excessive accumulation of uninhibited M1 macrophages.³³ Moreover, the fibroblast proliferation, function, and differentiation into myofibroblast also significantly reduced with suppressed expression of tumor growth factor β type II receptor and decreased collagen synthesis, which hindered the tissue remodeling stage.³⁴ The high glucose levels mediated-induction of matrix metalloproteinases-9 (which is responsible for collagen degradation and regulates keratinocytes migration) over-expression in diabetic models impaired keratinocyte migration.^{35,36} High glucose could also reduce the activity of VEGF and hypoxia-inducible factor 1 α (HIF-1 α), and increases the non-enzymatic glycation of many important proteins, leading to abnormal cellular and ECM function, thereby inhibiting angiogenesis in diabetic wounds.³⁷

General wound clinical therapies include restoration of skin perfusion, treatment of infection, metabolic control, treatment of co-morbidity and local wound care.³⁸ Although these standard treatments may achieve the goal of symptom control, but the effective treatment of diabetic wound healing remains limited. Moreover, traditional treatment mainly use dressings, the treatment process is long, easy to cause secondary injury, psychological and physiological adverse effect on diabetic patients. Currently, there are some technologies of wound healing treatment for diabetes, namely topical drug treatment (eg,

Figure 1 The physiological process of normal wound and diabetic wound. Unlike normal wounds, diabetic wounds are characterized by impaired angiogenesis, excessive inflammatory macrophages. Excessive production of matrix metalloproteinases (MMPs) at the wound site, and hyperglycemia leads to an increase ROS that prevent the formation of healthy tissue.

drugs, peptides and growth factors), cellular therapies (eg, stem cells and fibroblasts) and biomaterial-based treatment.³⁹ Biomaterials with controlled-release of signaling molecules can be combined with other therapeutic methods, which is a promising treatment method for diabetic wound healing.⁴⁰ In this review, we will summarize biomaterials and their potential applications in diabetic wound repair. In addition, we have also reviewed the challenges and application prospects of biomaterials in diabetic wound healing.

Substances Applied in Diabetic Wound Healing

Diabetic wounds often require a longer healing period due to persistent inflammation, bacterial infections, and degradation or diminished expression of growth factors.⁴¹ In addition, chronic hyperglycemia makes new vessel formation is difficult, thus limiting the access of oxygen and nutrients to the wound site.⁴² Therefore, some substances need to be delivered from the outside to promote the healing of diabetic wounds. At present, a variety of bioactive molecules (such as growth factors, genes/proteins/peptides, stem cells/exosomes, etc.) and non-bioactive

substances (metal ions, oxygen, nitric oxide, etc.) are widely used to promote diabetic wound healing (Figure 2).

Bioactive Molecules

Signaling Molecules

It is well known that chemokines can directly promote angiogenesis, ECM remodeling or formation and re-epithelialization.^{43,44} These chemokines play a crucial role in the migration of inflammatory cells and mesenchymal stem cells.⁴⁵ Moreover, the chemokines (interleukin-8, IL-8; macrophage inflammatory protein-3 α , MIP-3 α) that possess the ability to recruit bone marrow-derived mesenchymal stem cells (BMSCs) for articular cartilage repair.⁴⁶ In addition, IL-8 is also known to be a potent promoter of angiogenesis.⁴⁷ Previous studies have shown that horseradish peroxidase triggered in-situ cross-linked gelatin-hydroxyphenyl propionic acid (GH) hydrogels can be used as an injectable carriers for tissue engineering and regenerative medicine.^{48,49} Therefore, two types of chemokines (IL-8 and MIP-3 α) could be loaded into GH hydrogel.⁵⁰ IL-8/MIP-3 α was released through GH hydrogel within 7 days, and endogenous cells were able to attract chemokines to the wound. The incorporation of chemokines did

Figure 2 Schematic illustration of the categories of biomaterials used on diabetic wounds. Biomaterials are loaded with bioactive molecules (including GFs, genes/proteins/peptides, stem cells/exosomes, etc.) and non-bioactive substances (including metal ions, oxygen, etc.) to promote diabetic wound healing.

not affect hydrogels' properties (including swelling ratio and mechanical stiffness), and the bioactivities of IL-8 and MIP-3 α were stably maintained in GH hydrogel. GH/IL-8 and GH/MIP-3 α hydrogel dressings promote diabetic wound regeneration, enhance re-epithelialization/neovascularization and collagen deposition.⁵⁰ GH hydrogel can be used as a delivery platform for various therapeutic proteins for wound healing in the future.

Various growth factors are important function in mediating, coordinating and controlling cellular interactions during normal wound healing.⁵¹ But in diabetic wounds, the balance of many growth factors is upset, damaging angiogenesis, disrupting the ECM, and ultimately delaying wound healing (Figure 3). A strategy of mediating the diabetic wound cell signaling is to locally administering endogenous therapeutic growth factors.⁵² However, repeated high doses of growth factors are needed to achieve therapeutic effects.⁵³ And the proteases in the cells cause growth factors to degrade rapidly. Therefore, a delivery system is required not only to maintain growth factor activity, but also to enable sustained and controlled release of growth factors to the target. Currently, various systems (including nanoparticles, hydrogels and nanofibers) have been used for growth factors delivery in diabetic wound^{54–61} (Table 1).

Previous studies have shown that VEGF-A is the primary pro-angiogenic factor in normal healing wounds.⁶² Its expression reached a peak at 2–3 days after injury and continued to rise for about a week.⁶³ However, compared to normal mice, the increase of VEGF in db/db diabetes mice is transient, rather than sustained, and rapidly

decreases to almost undetectable levels when granulation tissue is formed.⁶⁴ The results of clinical trials showed that single-dose application of VEGF to wounds alone has limited success due to its short half-life.⁶⁵ Repeated local delivery of VEGF-165 promoted rapid re-epithelialization and enhanced angiogenesis of diabetic wounds.^{66–68} In order to overcome the disadvantages of short half-life and repeated delivery of VEGF, delivering VEGF by gene activation strategy should be effective. Physical encapsulation of nucleic acid-carrier complexes in a hydrogel can protect the carrier from degradation and provide more sustained, localized transfection compared with rapid delivery of growth factors or genes.⁶⁹ Hyaluronic acid (HA), the main component of the ECM, is a highly biocompatible biomaterial, which can also promote angiogenesis.⁷⁰ Porous HA hydrogel with encapsulated proangiogenic (pVEGF) plasmids for local gene therapy in diabetic wound healing.⁷⁰ These researches have shown that porous hydrogels did not degrade and provided a mechanical barrier to wound healing. However, transfection levels of pVEGF did not appear to be high enough to enhance angiogenesis by increasing vascular density or size.⁷⁰ Devalliere et al recombined keratinocyte growth factor (KGF) and cytoprotective peptides into a protein polymer with the aim of increasing their activity in vivo (enhancing anti-proteolytic ability), thereby accelerating chronic wound healing (increasing wound bed angiogenesis).⁷¹ Previous studies have shown that two or more growth factors are more effective at stimulating angiogenesis and subsequent tissue repair than a single growth factor.^{72,73} For example, co-

Figure 3 Changes in GFs in diabetic wounds. **(A)** Changes in growth factors in diabetic wounds and their effects on angiogenesis and ECM. **(B)** Hyperglycemia leads to the production of oxygen free radicals.

stimulation of VEGF-A and fibroblast growth factor 2 (FGF-2) significantly improves cell migration and angiogenesis in vivo compared to single angiogenic growth factor.⁷⁴ In addition, the delivery of bFGF and VEGF as dual factors immediately restored the vascular network.⁷⁵

In the future, local controlled delivery of multiple GFs by the combination of nanoparticles and hydrogels. At the same time, determine the optimal degradation rate of the hydrogel and reduce the toxicity of the nanoparticles to allow for overall faster wound closure.

Genes/Proteins/Peptides

Targeting disease-related miRNA may be an effective therapeutic strategy in comparison with single-target angiogenic growth factors, since an individual miRNA with its pleiotropic effects can regulate multiple different genes and processes⁷⁶ (Table 2). Recently, miR-26a has been identified

as a key negative regulator of angiogenesis in diabetic wounds, inhibition of this miRNA may be an effective treatment for diabetes.⁷⁶ Wu et al developed a redox-modulatory ceria nanozyme-reinforced self-protecting hydrogel (PCN-miR/Col).⁷⁷ PCN-miR/Col not only remodeled the oxidative wound microenvironment, but also ensured the structural integrity of the encapsulated pro-angiogenic miRNA in the oxidative microenvironment.⁷⁷ The design adopted the “seed-and-soil” concept in the regenerative medicine field with the aim to reshaping the oxidative wound microenvironment into a proregenerative one (the “soil”), and providing proangiogenic miRNA cues for diabetic wound repair and regeneration (the “seed”). The proposed “seed-and-soil” strategy is applicable to the repair and regeneration of a wide range of damaged tissues, which exposed to highly oxidative diseased microenvironments and dysfunctional biomacromolecules.⁷⁷ So, it is a new direction of treatment

Table 1 Growth Factors in Nanoparticles/Hydrogels/Scaffolds Used in Experimental Diabetic Wound Healing Studies

GFs	System	Results	Characteristic	References
IL-8 and MIP-3 α	Gelatin hydrogels	Enhanced reepithelialization and increased collagen deposition.	Stable bioactivity; in situ cross-linking.	[50]
bFGF and NGF	Heparin-poloxamer hydrogel	Facilitating schwann cell proliferation, enhanced axonal regeneration and remyelination.	Good affinity; controlled GFs release.	[54]
VEGF and bFGF	PLGA nanoparticles	Induced complete re-epithelialization, with enhanced granulation tissue formation and collagen deposition.	Control release of multiple GFs.	[58]
VEGF, PDGF, bFGF and EGF	Col-HA-GN nanofibrous membrane	Elevated collagen deposition and enhanced maturation of vessels.	A stage-wise release pattern of multiple angiogenic factors.	[59]
pVEGF plasmids	HA hydrogels	Promoted wound closure and induced an enhanced angiogenic response.	Local gene delivery.	[56,70]
SDF-I	PPCN hydrogel	Exhibited accelerated granulation tissue production, epithelial maturation, and the highest density of perfused blood vessels.	Antioxidant thermoresponsive.	[55]
KGF	Elastin biopolymers	Increasing angiogenesis in the wound bed and accelerating healing.	Increasing GFs proteolytic resistance, thus improve their activity in vivo.	[71]
rh-aFGF	Carbomer hydrogel	Remarkable promotion of skin wound healing in diabetic rats with full-thickness injuries.	Good biostability.	[57]
PDGF	Sheath-core nanofibrous PLGA scaffolds	Sustainably released PDGF, vancomycin, and gentamicin for three weeks.	Biodegradable sheath-core nanofibers.	[60]
EGF	OHA and SCS hydrogels	Promotion of fibroblast proliferation and tissue internal structure integrity, as well as the deposition of collagen and myofibrils.	pH-responsive hydrogel.	[61]

for diabetic wounds. Li et al had developed a β -CD-(D₃)₇ as the gene carrier to carry siRNA, which effectively interfered with the expression of MMP-9, accelerated wound healing and could not cause organ damage and accumulation.⁷⁸ The results suggest that this gene carrier might be developed as a novel topical agent for the diabetic wound treatment. See (Table 2) for other systems.^{79–81}

Although genes and growth factors are intended to improve angiogenesis and re-epithelialization, cost and safety issues remain in their application.⁸² Introduction of peptides into hydrogels or scaffolds has been widely used to confer these tissue-engineering substrates with bioactivity^{83–90} (Table 2). Carrejo et al prepared a multidomain peptide hydrogel that can rapid cell infiltration and elicit a mild inflammatory response, thereby promoting angiogenesis and accelerating wound closure in diabetes.⁹¹ A therapeutic integrin-binding pro-survival peptide-engineered silk fibroin nanosheet that can regulate angiogenesis and promote diabetic

ulcer healing.⁹² Nanofibrous mats of *Antheraea assama* silk-worm silk fibroin are coated with various recombinant spider silk fusion proteins through silk–silk interactions to fabricate multifunctional wound dressings.⁹³

We recently reviewed the roles of peptides in diabetic wound healing. Research spans the use of native proteins, recombinant proteins, and engineered peptides with integration in a diverse set of substrates from conjugation to hydrogel matrices. While the current studies have demonstrated the benefits of these strategies, the key consideration should be how to promote diabetic wound repair. A large number of clinical trials should be carried out to conduct an overall evaluation of the efficiency and safety of peptides in diabetic wound healing.

Stem Cells/Exosomes

Stem cells can produce various bioactive substances (such as growth factors) to restore tissue/organ function, so stem

Table 2 Genes/Proteins/Peptides Used in Diabetic Wound Healing are Summarized. Most of the Genes are miRNA, and There are Both Natural and Synthetic Peptides

Gene/Proteins/Peptides	Carrier System	Function	References
siRNA	β -CD-(D ₃) ₇ ; nanometer-scale coatings.	Decreasing MMP-9 expression.	[78,79]
Keap1 siRNA	Lipoproteoplex delivers	Activate Nrf2-mediated endogenous antioxidant mechanisms, normalize the ROS imbalance.	[81]
miR-26a	PCN hydrogel	Offer the proregenerative wound microenvironment and proangiogenic miRNAs.	[77]
Plasmid DNA encoding VEGF	Ga-BDEs	Enhance sustained expression of VEGF.	[80]
Heparin mimetic peptide amphiphiles	Nanofibers	Enhance production and activity of major angiogenic growth factors (VEGF).	[84]
DMOG	PCL fiber meshes	Reducing the expression of pro-inflammatory factors (IL-1 β , IL-6, and TNF- α), increasing anti-inflammatory factors (TGF- β 1 and IL-4) and GFs (IGF-1, HB-EGF, NGF, and bFGF), and promoting angiogenesis (CD-31 and VEGF- α).	[86]
K ₂ (SL) ₆ K ₂	MDP hydrogels	Allowing rapid cellular infiltration, and thus are ideal for tissue engineering strategies.	[91]
Proline	IKFQFHFD hydrogel	Eradicate MRSA biofilm.	[85]
Spider silk fusion proteins	Nanofibrous mats of AaSF	Efficient matrix remodelling of wounds.	[93]
Heparin or bemiparin	CS hydrogels	Improved diabetes-associated impaired wound healing.	[87]
Nucleic acids	tFNAs	Antioxidant activity via the Akt/Nrf2/HO-1 signaling pathway.	[88]
Integrin	Silk fibroin nanosheets	Regulate angiogenesis and promote diabetic ulcer healing.	[92]
Laminin mimetic peptide SIKVAV	CS hydrogels	Significantly promoted BMSCs adhesion and proliferation.	[89]
MMP-9 inhibitor (R)-ND-336	Linezolid	Inhibiting the detrimental MMP-9, mitigating macrophage infiltration to diminish inflammation	[90]

cell therapy is one of the most promising methods for diabetic wounds^{94–101} (Table 3). Epidermal growth factor (EGF)-loaded microcapsules and human adipose-derived stem cells (ADSCs) are integrated into the collagen hydrogel and facilitate tissue regeneration and effectively restore blood perfusion.¹⁰² Moreover, acrylated hyaluronic acid (AHA) hydrogels load pluripotent stem cells (hiPSCs) treat type-1 diabetic wounds.¹⁰³ In addition, gingival mesenchymal stem cells (GMSCs) loaded into the chitosan/silk hydrogel sponge effectively promote the skin wound healing.¹⁰⁴ With the capacity to protect and

regulate immune function during the healing process, macrophages (M Φ) especially M Φ 2, contribute to reduce inflammation and promote proliferation and angiogenesis by releasing anti-inflammatory cytokines and growth factors (such as TGF- β and VEGF).⁹⁷ Although the pullulan–collagen composite hydrogel has been reported to deliver monocytes or macrophages to the wound bed, the interaction between immune cells and the material is unclear. Liu et al have reported a 0.5Cu-HHA/PVA@M Φ 2 hydrogel to provide and regulate M Φ 2 for synergistic improvement of immunocompromise and impaired angiogenesis to

Table 3 Summary of Stem Cell/Exosomes Towards Effective Control of Diabetic Wounds

Cell Types	Systems	Characteristic	References
SMSC exosomes	CS Wound Dressings	Overexpression microRNA-126-3p exosomes.	[118,119]
AMSCs exosomes	OHA hydrogels	Bioactive multifunctional properties (injectability, self-healing, antibacterial activity, stimuli-responsive exosomes release).	[116]
GMSCs Exosomes	CS/Silk hydrogel sponge	Combination of GMSC-derived exosomes and hydrogel.	[114]
ASCs exosomes	FEP dressing	Injectable adhesive thermosensitive multifunctional dressing.	[117]
hASC exosome	hASC-exos carrying miR-21-5p as a cargo by electroporation	Combination of ASC-exos with miR-21 to achieve synergetic therapeutic.	[115]
hiPSCs	AHA hydrogels	Engineering vascularized constructs.	[103]
ASCs	PEG-gelatin hydrogel	Delivery of allogeneic ASCs in vivo.	[95]
MSCs	RGO nanoparticles	Acellular dermal composite scaffold.	[96]
ADSCs	GSL cryogels	Delivering ADSCs on antioxidant GS scaffolds coated with GSL, an endothelial basement protein to improve angiogenesis.	[98]
M2 phenotype macrophages	HHA hydrogel	Multiple modulation mechanisms of immunocompromise and angiogenesis.	[97]
Decellularized ECM	dECM hydrogels	Hydrogels derived from genetically engineered.	[100,101]
ECM-biomimetic cell-free nanofibrous	Bone ECM-biomimetic nanofibrous scaffolds	Without additional growth factors.	[99]

accelerate the diabetic chronic wound healing phase transition from inflammation to proliferation and remodeling.⁹⁷ Hydrogels facilitate the adhesion, growth, migration and regeneration of immune cells.

Exosomes are nanoscale membrane vesicles (30–150nm in diameter) that can be identified by the expression of exosome-related markers (such as *Alix*, *Tsg101*, *CD9*, *CD63* and *CD81*) and carry functional complexes of proteins, lipids and nucleic acids.^{105–108} Therefore, exosomes are considered as drug delivery carriers, and natural RNA carriers for the treatment of diseases.^{109–111} And exosomes are considered as one of the most important secretory products of bone marrow mesenchymal stem cells, which can mediate intercellular communication and promote wound healing.^{112–115} Polypeptide-based FHE hydrogel (F127/OHA-EPL) contains adipose-derived mesenchymal stem cell exosomes (AMSCs-exo),¹¹⁶ FHE@exo hydrogel has multifunctional properties of biological activity, including injectability, self-healing, antibacterial activity, and exosome release. And it can significantly improve the proliferation, migration and angiogenesis of human umbilical vein endothelial cells (HUVECs). FHE@exo hydrogel promotes neovascularization and cell proliferation, leading to faster granulation tissue formation, re-epithelialization, and collagen remodeling at wound sites, thus accelerating the

healing process of diabetic wounds.¹¹⁶ Wang et al developed an injectable thermosensitive multifunctional polysaccharide-based dressing (FEP) with sustained pH-responsive exosome release that promotes angiogenesis and diabetic wound healing.¹¹⁷ Moreover, hydroxyapatite/chitosan or chitosan hydrogel incorporating microRNA-126-overexpressing synovium mesenchymal stem cells (SMSC-126-Exos) can accelerate re-epithelialization, stimulate the proliferation of human dermal fibroblasts, and activate angiogenesis.^{118,119} Exosome-based hydrogels hold great promise in the treatment of chronic wounds (especially diabetic wounds) and skin regeneration. Therefore, it may become a treatment means in the future.

Drugs

Under the framework of pharmaceutical and clinical challenges of drug delivery in diabetic wound infections, an ideal drug delivery system must deliver the drug in deep layers of skin. The nanoscale local drug delivery system, combined with hydrogel/nanoparticles properties, can stabilize the long-term release of drugs to the wound and promote healing.¹²⁰ At present, a variety of complex delivery systems have been developed to extend drug delivery time^{121–126} (Table 4). A multi-responsive composite polydopamine/nanocellulose hydrogel with the ability of drug

Table 4 Delivery of Drug/Natural Macromolecular Bioactive Substances Systems with Effective Control of Chronic/Diabetic Wounds

Drugs/	Drug Delivery Systems	Functions	References
Deferoxamine(DFO)	TDDS; multifunctional hydrogels; nanofibrous/scaffolds.	Increases HIF-1 α expression; upregulate VEGF expression.	[132–134]
Statins	Tissue engineering scaffold	In situ eNOS/NO up-regulation.	[121]
Insulin	Injectable hydrogels	pH and glucose dual-responsive hydrogels.	[137]
Curcumin	Gelatin microspheres; chitosan nanoparticles.	MMP9-responsive drug-release system; anti-inflammatory and antioxidant.	[139–141]
Dimethyloxalylglycine (DMOG)	Porous electrospun fibrous membrane	Controllable released DMOG drugs	[138]
Ciprofloxacin	CS and cyclodextrin polymer sponges	local drugs release without risk of toxicity to the body.	[122]
Snail glycosaminoglycan	Sulfated polysaccharide	Accelerated the healing of full-thickness wounds in diabetic mice skin.	[123]
Kirenol	Diterpenoid	Encourage angiogenesis, fibroblast propagation	[124]
Quercetin	Collagen-nanomaterial-drug hybrid scaffold	Promoting collagen deposition and angiogenesis in diabetic wound repair.	[125]
Herbal extract of didymocarpus pedicellatus	pDMAEMA–HA hydrogel	Enhanced cutaneous wound repair as well as high level of cellular repair.	[126]

(tetracycline hydrochloride) release and wound healing.¹²⁷ The drug can be released continuously for more than 24 hours, and no explosive drug release occurs at the beginning of the release process. The maximum drug release ratio reached 77%, with long-term drug delivery properties.¹²⁷ Desferrioxamine (DFO) is used as

a hypoxic-mimetic agent, and has been used for the induction of HIF-1 α accumulation.^{128–130} And HIF-1 α has been shown to play an important role during the wound healing.¹³¹ DFO-loaded hydrogel/scaffolds by upregulating HIF-1 α that rapidly promote angiogenesis for diabetic skin regeneration^{132–134} (Figure 4). In addition, mixed

Figure 4 Development of a transdermal drug delivery system for DFO. (A) DFO patch is administered through transdermal drug delivery system into the dermis to perform its functions. (B) Functional diagram of DFO and its regulation in the HIF-1 α signaling pathway.

DFO and bioglass (BG) in sodium alginate hydrogel, BG and DFO could synergistically upregulate HIF-1 α and VEGF expression, and subsequently vascularization in the wound sites, and better facilitate diabetic skin wound healing.¹³⁵ Insulin is a universal drug for treating diabetes because it is a physiological glucose-lowering agent. The use of topical insulin became of greater interest as a healing agent in diabetic foot ulcers.¹³⁶ However, the use of topical insulin presents a great challenge due to the instability of the molecule. In order to ensure molecular stability of insulin, it is incorporated into hydrogels to maximize its effect. Recently, the drug- and cell-loaded hydrogels have promising potential in wound healing. Protein drugs (insulin) and live cells (fibroblasts L929) can be encapsulated in the pH and glucose dual-responsive injectable hydrogels, this hydrogel dressing could promote neovascularization and collagen deposition and enhance the wound-healing process of diabetic wounds.¹³⁷ The combination of drugs and cell/growth factors hydrogel may be a promising approach to enhance wound healing and can also be used for the regeneration of other vascularized tissues. A kind of aligned porous poly (L-lactic acid) electrospun fibrous membranes loaded mesoporous silica nanoparticles that release dimethylloxalylglycine for diabetic wound healing.¹³⁸ Encapsulation of curcumin nanoparticles with MMP9-responsive and thermos-sensitive gelatin microspheres hydrogel improves diabetic wound healing.^{139–141}

Improving some properties of composite scaffolds/hydrogels can increase drug load and control drug release. When scaffolds/hydrogels are subjected to certain stimulation (near infrared laser irradiation or pH), drugs are released in “on-off” mode without explosive drug release at the beginning of the release process, and has long-term drug delivery performance. In the future, our research direction should be precise administration, which can be achieved gradually at different stages of wound healing. Wound-healing research will need to incorporate hydrogels, which can deliver more DNA, growth factors, peptides and drugs, increasing angiogenesis and wound healing. It is also important to determine the optimal hydrogel degradation rate and water content for faster wound healing, while maintaining complex release and mechanical support to the wound bed. However, emerging drug resistance and physicochemical characteristics require the design of more accurate topical drug delivery systems which could be combined with 3D technology to achieve high functional efficiencies in terms of permeability, stability and therapeutic efficacy.

Non-Bioactive Elements

Metal Ion

Currently, the antibacterial nanoparticles used in wound healing are silver nanoparticles, gold nanoparticles, copper nanoparticles, nano-bioactive glass particles, etc.^{142–147} Among different metal nanoparticles, AgNP is the most active nanoparticle due to its unique anti-inflammatory properties and antibacterial activity against natural and nosocomial strains of multidrug-resistant (MDR) microorganisms, promoting wound healing.¹⁴⁸ The mechanisms of antimicrobial action of AgNPs are of two types, (a) the inhibitory action and (b) the bactericidal action.¹⁵ Such as NIR laser-excited silver triangular nanoparticles (Tri-Ag) can eradicate multidrug-resistant bacteria and promote wound healing.¹⁴⁹ Tong et al constructed a combinational antibacterial system by loading AgNPs on the polydopamine-modified prussian blue NPs(PB@PDA@Ag), the bactericidal mechanism of this system can be attributed by damaging cell integrity, producing ROS, the reducing ATP and disrupting bacterial metabolism.¹⁵⁰ Likewise, Zhao et al used polydopamine decorated silver nanoparticles, and then loaded into conductive hydrogel to inhibit bacterial growth and control diabetic wound infection.¹⁵¹ Gold NPs (AuNPs) can perform gene transfer, drug delivery, as biosensors and cancer cell imaging, angiogenesis as well as wound healing.^{152–155} AuNPs could inhibit the lipid from peroxidation and prevents the formation of ROS to restores antioxidant discrepancies.¹⁵ AuNP combines with epigallocatechin gallate (EGCG) or alpha-lipoic acid (ALA) or both (EA) to achieve synergistic effects and enhance diabetic wound healing by modulating angiogenesis and anti-inflammatory effects.^{156,157} Wang et al optimized a novel gene delivery system based on antimicrobial peptide (LL37) grafted ultra-small gold nanoparticles for the topical treatment of diabetic wounds with or without bacterial infection.¹⁵⁸ Copper nanoparticles (CuNPs) have been gained increasing attention due to its antibacterial activity in diabetic foot ulcer infections^{159,160} (Table 5). Bhadauriya et al focused on the synthesis of the yeast extract-immobilized and copper nanoparticle-dispersed carbon nanofibers as a potential diabetic wound dressing material.¹⁶¹ Copper-based metal-organic framework nanoparticles can be modified to slowly release Cu²⁺, which reduces toxicity and improves wound healing in diabetes.^{147,159,160} However, rapid oxidation and agglomeration of copper nanoparticles are key problems during their use, and needs to control the stability of CuNPs by using biocompatible stabilizer such as chitosan and folic acid.^{159–161}

Table 5 Metallic and Metal Oxide Nanomaterials are Used in Diabetic Wound Repair

Metal Ion	Delivery Systems	Relative Merits	References
Silver	PB@PDA@Ag nanosystem; PDA@Ag NPs/CPHs hydrogels	1.Eradicating MRSA assisted with NIR; 2.Epidermal sensors	[145,146,150,151]
Copper	HKUST-I NPs; Cu-CNF-YE nanofiber; BSA-CuS nanoparticles	1.Decrease copper ion toxicity and apoptosis; 2.Simultaneous control of bacterial infections; 3.As a controllable NO-releasing vehicle.	[147, 159–161, 213]
Gold	AuNPs@LL37	1.A novel gene delivery system; 2.Topical treatment of diabetic wounds with or without bacterial infection	[158]
Rubidium	Rb-CA gel hydrogel	Rb-CA gel exhibited a strong anti-inflammatory effect on the wound.	[208]
Si and Ca ions	BG/AA hydrogel; BG/PEM membrane;	1.BG particles stimulated macrophage proliferation; 2.Improve the angiogenic condition of the wound area.	[163,164,167,168]
Iron –Copper	Bimetallic Fe-Cu nanocomposite	1.Antimicrobial activity; 2.wound healing property	[165]
nCeO	PHBV membrane	Enhance cell proliferation and vascularization	[210]
MoS2	MoS2-BNN6 nanovehicle	MoS2-BNN6 nanovehicle can precisely control NO release, generating oxidative/nitrosative stress.	[212]
NAGEL particles	PCL/gelatin nanofibers scaffold;	1.Released Si ions; 2.Synergetic effect on the improved efficiency of diabetic wound healing.	[162,169]

In recent years, bimetallic/polymetallic composite nanomaterials have great potential in diabetic wound repair.^{162–164} Das et al reported a bimetallic (Fe-Cu) wound healing dressing material that exhibited antimicrobial activity against methicillin-resistant *Staphylococcus aureus* and displayed in vivo diabetic wound healing property.¹⁶⁵ Bioactive glass (BG), which is typically composed of Na₂O, SiO₂, CaO and P₂O₅, is considered to be a classical material for hard tissue regeneration.¹⁶⁶ The ionic products of bioglass dissolution stimulate macrophages to secrete anti-inflammatory factors.¹⁶⁷ Zeng et al combined bioglass and sodium alginate for diabetic wound healing.¹⁶⁸ Jiang et al found that the Si ions released by bioactive glass up-regulated the expression of VEGF.¹⁶⁹

In the future, the reversible swelling-shrinking transition of hydrogels can be utilized to achieve controllable and sustained release of Ag⁺, Cu²⁺ and Si²⁺ etc., so as to avoid the explosive ion release causing damage to cells. This system has great potential in tissue repair and antibacterial application.

Oxygen

Chronic diabetic wounds are limited in oxygen supply due to vascular dysfunction and neuropathy.¹⁷⁰ In addition,

high oxygen consumption by cells during inflammation also leads to hypoxia in the wounds. Due to the increased utilization of oxygen in some regenerated tissues, there are inevitable differences between the supply and demand of oxygen, and the result is a hypoxic environment with high oxidative stress.¹⁷¹ In addition, increased oxidative stress in diabetic ulcers is caused by macrophages and neutrophils producing more ROS in a hyperglycemic response.^{172,173} Hence the need for multifaceted biomaterials that will simultaneously reduce the oxidative stress, provide oxygen, and induce angiogenesis. To reduce oxidative stress, Zhu et al developed a thermoresponsive antioxidant poly(polyethylene glycol co-citric acid-co-N-isopropylacrylamide) hydrogel (PPCN) that uses the laminin-derived dodecapeptide A5G81 (PPCN-A5G81). A5G81 peptide conjugation to PPCN via the cross-linker N-β-maleimidopropionic acid hydrazide. A5G81 has unique receptor-mediated and antioxidant properties and is beneficial to the diabetic wound repair.¹⁷⁴ Novel nanofibrous mats (chitosan/poly (vinyl alcohol)/ZnO nanofibrous) with antibacterial and antioxidant properties for diabetic wound healing,¹⁷⁵ but the mechanism of the

healing of diabetic wounds caused by nanofiber mats has not been clarified in this study.

Oxygen Containing Nanocarriers

At present, oxygen-producing materials are mainly delivered through some nanoscale systems to relieve wound hypoxia. The main oxygen-producing materials are sodium percarbonate (SPO), calcium peroxide (CaO_2), magnesium peroxide (MgO_2), hydrogen peroxide (H_2O_2), and fluorinated materials.^{176–180} It has been shown that the combination of nanomedicine and some oxygen-producing agents can improve the wound healing of diabetes.³⁰ Recently, Shiekh et al developed a porous cryogels (polyurethane polymeric material-calcium peroxide, PUAO-CPO), PUAO-CPO cryogels can not only continuously release oxygen, but also supplement with adipose-derived stem cell (ADSCs) exosomes¹⁸¹ (Figure 7B). Nanoperfluorocarbon (nano-PFC) has been widely studied as an oxygen-carrying system to overcome hypoxia-associated resistance in cancer therapies due to its high oxygen affinity and good biocompatibility.^{182–184} In addition, PFC has been approved by the USA Food and Drug Administration (FDA) to improve myocardial oxygenation and prevent ventricular dysfunction.^{185,186} Therefore, nano-PFC can be used as a nano-drug delivery system (NDDS) to deliver molecules, such as drugs and oxygen to target tissues, and release the contents under the stimulus of external conditions.^{187,188} Wang et al combined the radial extracorporeal shock wave therapy (rESW) with oxygen-carrying nano-PFC to provide targeted oxygen supply, improving blood microcirculation of DFUs and accelerating wound healing.¹⁸⁹ And when nano-

PFC is injected into the blood circulation, the nanodroplets triggered by rESW can reversibly release oxygen within the tumor tissue¹⁸⁹ (Figure 8C). This strategy offered a great potential for further clinical trials. However, the potential safety problems of PFC-based micro/nanomaterials cannot be ignored. Therefore, a large number of experiments are needed to further prove its reliability. In addition, Zehra et al developed a polycaprolactone (PCL)-based oxygen-releasing electrospun wound dressings. The dressing can produce oxygen continuously for up to 10 days and stimulate angiogenesis.¹⁹⁰ These oxygen-loading nanomaterials can improve wound healing efficiency. Therefore, oxygen-producing biomaterials are essential to cure chronic diabetes wounds in the future^{191–194} (Table 6).

Hydrogen Sulfide Containing Nanocarriers

Besides, the synthesis and levels of circulating hydrogen sulfide (H_2S) are reduced in diabetic mellitus.¹⁹⁵ Studies have shown that H_2S can stimulate cell proliferation and migration and regulate ECs assembly into capillary structures.¹⁹⁶ Therefore, exogenous H_2S supplementation is a promising treatment method to promote refractory wound healings in diabetic. Lin et al used emulsion technique to prepare NaHS particles (NaHS@MPs), which could be used as in situ depot for continuous release of exogenous H_2S under physiological conditions.¹⁹⁷ The sustained release of H_2S from NaHS@MPs promotes several cell behaviors, including epidermal/endothelial cell proliferation and migration, as well as angiogenesis, by extending the activation of cellular ERK1/2 and p38,

Table 6 Summary of Current O_2 Delivery Systems

Materials	Delivery Systems	Functions	References
Perfluorocarbon	Nano-PFC	The targeted release of oxygen into the wound from oxygen-loaded Nano-PFC	[189]
MNs with oxygen carrying	GelMA tips	Oxygen carrying and controllable oxygen delivering ability for wound healing	[191]
Calcium peroxide	OxOBand; PGS/PCL nanofibers; scaffolds; OGA hydrogel	Delivering oxygen, inducing angiogenesis, and management of oxidative stress and infection	[181,192–194]
Sodium percarbonate	PCL nanofibers scaffolds	Continuously generating oxygen for up to 10 days	[190]
Sodium hydrosulfide	NaHS@MPs	NaHS@MPs sustained release of exogenous H_2S under physiological conditions	[197]
Nitric oxide	DNICs	Continuous release of nitric oxide	[201]

accelerating the healing of full-thickness wounds in diabetic mice.¹⁹⁷

Nitric Oxide Containing Nanocarriers

NO is an antibacterial agent effective against a broad range of bacteria, including biofilm forming microorganisms, through an oxidation process involving free radical superoxide ($O_2^{\bullet-}$) to form peroxynitrite ($-OONO$).¹⁹⁸ Nitric oxide (NO) plays a key role in the physiological regulation of vascular function, but in diabetic patients, NO synthesis and bioavailability decrease as well as NO consumption increases.^{199,200} A direct and effective strategy for promoting diabetic skin ulcer healing is exogenous supplement of NO. Chen et al activated the NO-sGC-cGMP pathway by inducing long-term NO release ($t = 27.4 \pm 0.5$ h at 25°C and 16.8 ± 1.8 h at 37°C) and maintaining the angiogenesis process.²⁰¹

Technology Nanoparticles

Nanoparticle (NP) is a basic component of nanostructure and has its unique size and characteristics.²⁰² NPs applications mainly include drug and gene delivery, tissue engineering and fluorescent biological labels, etc.^{203–206} (Figure 5). Currently, the NPs used in diabetics wound healing mainly include metallic and metal oxide nanomaterials, nonmetallic nanomaterials (Table 7). NPs and nanotechnology allow them to achieve high local drug

concentrations with relatively few side effects compared to traditional drug delivery systems, so drug therapy is more effective. There are two main criteria of nanomaterials used in wound healing (1) nanomaterials that are beneficial to wound healing; (2) nanomaterials as delivery vehicles.

Metallic and Metal Oxide Nanomaterials

The antibacterial mechanism of silver is realized by blocking the respiratory enzyme pathways and altering the microbial DNA and cell wall.¹⁵ Tong et al promoted diabetic wound healing through the antibacterial of silver ions.¹⁵⁰ Copper ions can also stimulate angiogenesis and collagen deposition processes in addition to antibacterial effects, thus improving diabetic wound healing.^{159–161} Rubidium (Rb) is an important microelement for the human body. Rb^+ has been reported to inhibit or kill bacteria by affecting membrane potential.²⁰⁷ He et al loaded rubidium into calcium alginate hydrogel to achieve antibacterial and promote diabetic skin wound healing.²⁰⁸ The intrinsic antibacterial properties of zinc oxide nanoparticles (nZnO) prompt the use of these nanomaterials in several hydrogel-based wound dressings.²⁰⁹ Cerium oxide nanoparticle incorporated electrospun membranes for diabetic wound healing.²¹⁰ However, despite the high potential of metallic nanoparticles in treating drug-resistant bacteria, the high toxicity of these materials limits their use in wound healing.²¹¹ In addition, Gao et al have reported a new near-infrared 808nm laser-mediated nitric

Figure 5 The major applications of nanoparticles.

Table 7 Other Approaches for Diabetic Wound Repair

Technology	Systems	Results	References
NPs	Chitosan/PVA Nano fiber; CW/NPs/HBC-HG hydrogel; MEL-NPs; CS/PVA/ZnO nanofibrous membranes.	Substrate does not have any recognized cytotoxicity; antibacterial properties.	[175,222–224]
	rGO; ADM-GO-PEG/Que.	Enhanced angiogenesis, collagen synthesis, and deposition in treated wounds.	[125,214]
	pSi NPs.	FnAb-loaded pSi NPs treated with proteases show intact and functional antibody for up to 7d post-treatment.	[220]
3D printing	A top layer made of silver-loaded gelatine cryogel; a bottom layer made of PDGF-BB-loaded 3D printed Gel scaffold.	The substrate was able to promote reepithelialization, granulation tissue formation, collagen deposition and angiogenesis in vivo.	[248]
	Satureja cuneifolia-loaded SA/PEG scaffolds.	3D printed scaffolds have shown an excellent antibacterial effect	[262]
	Microneedle patches.	Regulated the blood glucose levels of diabetic mice in normoglycemic ranges for up to 40 h	[263]
	Radially or vertically aligned nanofibers in combination with BMSCs.	Enhancing the formation of granulation tissue, promoting angiogenesis, and facilitating collagen deposition.	[249]
	PCL hydrophobic outer layer; Gel-pio inner layer.	Exhibit excellent ability to waterproof and prevent bacterial adhesion.	[250]
	Four-layer composite dressing (PU and dCA).	Not only allows wound exudates transport from wound bed to the dressing, but also enables controlled backflow of bioactive ion containing fluid to the wound bed for stimulating angiogenesis.	[251]

oxide-releasing nanovehicle (MoS₂-BNN6), MoS₂-BNN6 can effectively inhibit the growth of ampicillin-resistant *Escherichia coli*, heat-resistant *Escherichia faecalis*, and pathogen *Staphylococcus aureus*.²¹² Zhao et al used bovine serum albumin stabilized-CuS (BSA-CuS) NPs to propose that PTT could kill bacteria in the field of diabetic wound infection²¹³ (Figure 6). See Table 5 for detailed description of metal ion nanoparticles.

Nonmetallic Nanomaterials

A recent study reported that the use of graphene oxide (rGO)-isabgol nanocomposite dressings for enhanced vascularization and accelerated wound healing in normal and diabetic rats.²¹⁴ Furthermore, a study has shown that the different adhesion and bioactivity properties of GO can prevent bacterial adhesion and biofilm formation. Therefore, there is a growing interest in studying the potential of graphene-based materials in biomedical applications, such as drug delivery, tissue engineering, imaging, biosensing and wound healing.^{125,215,216} Porous silicon (pSi) is

a biological material widely used in vivo and in vitro.²¹⁷ pSi has the ability to store and release a variety of small molecular drugs, oligonucleotides, and even protein therapeutics.^{218,219} The use of porous silicon nanoparticles (pSi NPs) is demonstrated for the controlled release of Flii neutralizing antibodies (FnAb) to diabetic wounds.²²⁰ The use of nanotherapeutic drugs alone may cause rapid degradation and cannot reach the target tissue quickly and effectively, thus reducing the biological effect.⁵⁸ Xie et al used a dual-growth factor releasing nanoparticle-in-nanofiber system, encapsulated platelet derived growth factor in NP, embedded into VEGF nanofiber, and delivered VEGF quickly and PDGF in a relayed manner. Nanofiber/nanoparticle scaffolds significantly accelerate wound healing by promoting angiogenesis, increasing reepithelialization, and controlling granulation tissue formation.²²¹

Naturally occurring polymers, such as chitosan nanoparticles, have been studied for their antibacterial activity and pro-wound healing properties.^{222,223} Correa et al reported a melatonin loaded lecithin-chitosan

Figure 6 Schematic diagram of BSA-CuS antibacterial therapy. Reprinted with permission from Zhao Y, Cai Q, Qi W, et al. BSA-CuS nanoparticles for photothermal therapy of diabetic wound infection in vivo. *Biol Chem Chem Biol*. 2018;3:9510–9516. Copyright 2018, John Wiley and Sons.²¹³ (A) HRTEM image of the BSA-CuS nanoparticles. (B) Schematic illustration of BSA-CuS nanoparticles as photothermal agent for photothermal antibacterial therapy in vitro and in vivo.

nanoparticles improved the wound healing in diabetic rats.²²⁴ Chitosan composites usually exhibit unique properties that are not individually displayed by chitosan or the incorporated materials.^{175,225}

Currently, nanocarriers have been validated in vitro and offered potential therapeutic applications that require to be further tested in vivo. At the same time, several nanotherapeutic agents are used in combination with NPs (loaded copper, which is helpful for wound healing) to provide synergistic effect and accelerate wound healing.

Smart Hydrogels

Hydrogels are considered to be three-dimensional nanofiber materials composed of cross-linked hydrophilic polymer networks.⁴⁶ Due to the presence of chemical or physical cross-links, they are able to swell and retain large amounts of water, and preserving their structural and dimensional constrained integrity.⁴⁷ Hydrogels are biocompatible and biodegradable materials and have been used in cell therapy, drug delivery, biosensing, tissue engineering and wound healing^{226–229} (Table 8).

Injectable Hydrogels

In recent years, injectable hydrogels have favored among researchers due to its nonsurgical treatment to the patients for the purpose of mini-invasive medicine, especially for deep, irregular injuries.^{230,231} To enable injection, most in situ forming hydrogels are delivered in a liquid form that will subsequently solidify in the body.^{232,233} Typically, the injected precursor gel solution forms a hydrogel via

chemical (eg, Michael-type addition reaction, disulfide bond formation, click chemistry, radical polymerization) or physical (eg, ionic interactions, hydrogen bonding, hydrophobic interactions) crosslinking.^{234,235} Chen et al developed injectable self-healing and antibacterial hydrogel, the multi-functional hydrogel featured manageable, resistant to mechanical irritation, antibacterial and angiogenic properties. Hydrogel would show great promise in the physiological dysfunction and bacterial infection wounds.²³⁶ However, further studies are needed on the release and cytotoxicity of silver ions. Wang et al developed multifunctional hydrogel (injectable, self-healing, and adhesive) that simultaneously eliminated MRSA infection, reduced hyperglycemia, improved oxidative stress, and continuously provided oxygen.²³⁷ In addition, Kong et al loaded desferrioxamine and bioglass into injectable sodium alginate hydrogel to synergistic promote diabetic wound healing.¹³⁵

There have been many reports on wound dressing with bioactive/non-bioactive substances (growth factors, stem cells/exosomes and oxygen, etc.) for diabetic wound, but few studies have considered the specific physiological environment (such as acidic pH, ROS and high glucose levels) of diabetic wounds. Li et al reported a pH and glucose dual-responsive injectable hydrogel by in situ crosslinking of modified chitosan and oxidized dextran, and then Zhao et al incorporated insulin and fibroblasts into the hydrogel, which could not only respond to pH and glucose, but also promote wound healing in diabetic wounds.^{137,238} Zhu et al used zwitterionic hydrogel to monitor pH value and glucose concentration in diabetic

A

B

Figure 7 Schematic diagram of hydrogel synthesis. **(A)** Scheme of poly-carboxybetaine (PCB) hydrogel dressing for the detection of pH value and glucose concentration in wound exudate. Reprinted with permission from Zhu YN, Zhang JM, Song JY, et al. A multifunctional pro-healing zwitterionic hydrogel for simultaneous optical monitoring of pH and glucose in diabetic wound treatment. *Adv Funct Mater.* 2019;1905493. Copyright 2019, John Wiley and Sons.²³⁹ **(B)** The formation of OxOBand from PUAO-CPO cryogels with ADSC-exos. Reprinted with permission from Shiekh PA, Singh A, Kumar A. Exosome laden oxygen releasing antioxidant and antibacterial crygel wound dressing OxOBand alleviate diabetic and infectious wound healing. *Biomaterials.* 2020;249:120020. Copyright 2020, Elsevier.¹⁸¹

Abbreviations: HRP, horseradish peroxidase; DCF, dichlorofluorescein; GOx, glucose oxidase; H₂DCF, 2,2'-dichlorofluorescein-diacetate.

wounds, and these two parameters are converted into visible images, which were collected by smartphones and monitor changes in wounds at any time²³⁹ (Figure 7A). This multifunctional wound dressing may open vistas in chronic wound management and guide the diabetes treatment in clinical applications.

Conductive Hydrogels

In recent years, conductive hydrogels have also been widely used in health recording electrodes, biomedical patches, wearable/implantable bio-devices, and electronic skin.^{240–244} Conductive hydrogels are stimulated by external electrical signals, which are converted to bioelectrical stimulation after

Figure 8 Schematic diagram of material synthesis. **(A)** Schematic of the hierarchical structure of LbL films into a single coating. The first (X) film is a hydrolytically degradable undercoating, while the second (Y) film contains the siRNA to be delivered. **(B)** Side-on schematic of hierarchical LBL film architecture. Reprinted with permission from Castleberry SA, Almquist BD, Li W, et al. Self-assembled wound dressings silence MMP-9 and improve diabetic wound healing in vivo. *Adv Mater.* 2016;28:1809–1817. Copyright 2016, John Wiley and Sons.⁷⁹ **(C)** Schematic illustration of the synthesis procedure and rESW-responsive oxygen release from Nano-PFC. Adapted from Wang S, Yin C, Han X, et al. Improved healing of diabetic foot ulcer upon oxygenation therapeutics through oxygen-loading nanoperfluorocarbon-triggered by radial extracorporeal shock wave. *Oxid Med Cell Longev.* 2019;2019:5738368. Creative Commons license and disclaimer available from: <http://creativecommons.org/licenses/by/4.0/legalcode>.¹⁸⁹

reaching the skin to achieve the purpose of treatment. Zhao et al developed a conductive hydrogels (good self-healing ability as well as repeatable adhesiveness), which can promote angiogenesis, collagen deposition, inhibit bacterial growth and control diabetic wound closure.¹⁵¹ Zhang et al designed

conductive hydrogels based on polyvinyl alcohol and chitosan, the conductivity can enable hydrogels to perceive temperature and strain.²⁴⁵ The hydrogels are expected to build flexible sensory systems and the next generation of intelligent biomedical products in the future.²⁴⁵ Researchers are now focusing

Table 8 To Summarize the Role of Multifunctional Hydrogel in Diabetic Wound Healing

Smart Hydrogels	Peculiarity	References
Phenylboronic-modified CS, PVA and benzaldehyde-capped poly(ethylene glycol) hydrogels.	pH and glucose dual-responsive injectable hydrogels.	[137,238]
PDA@Ag NPs/polyaniline, and PVA hydrogels.	Skin-inspired antibacterial conductive hydrogels; good self-healing ability as well as repeatable adhesiveness.	[151]
Calcium silicate nanowires, SA, and OPO hydrogel scaffolds.	Excellent and controlled photothermal ability.	[247]
SH-PEG and silver nitrate hydrogel.	Injectable self-healing coordinative dynamic multifunctional hydrogel.	[236]
EPL-coated MnO ₂ nanosheets and insulin-loaded FCHO hydrogel.	Injectable multifunctional hydrogel.	[237]
Polypyrrole or Zn-functionalized CS PVA hydrogel.	Highly stretchable and conductive self-healing hydrogel.	[245]
PCB hydrogel.	Multifunctional pro-healing zwitterionic hydrogel; simultaneous optical monitoring of pH and glucose.	[239]
SA hydrogel.	Bioactive injectable hydrogels.	[135]
PVA-based hydrogel.	ROS-scavenging hydrogel.	[246]

on developing smarter hydrogels that not only contain “sensor” moieties that can respond to wound environmental pH, ROS levels, glucose concentrations, etc., but also are easy to operate and safe, this smart drug delivery system can promote diabetic wound healing.^{246,247}

Although significant progress has been made in injectable hydrogels, more research is needed to address some of the current technical challenges. A major limitation of injectable gels is the rapid release of low molecular weight compounds such as drugs and biomolecules. One way to slow down the kinetics of drug release is to hybrid the hydrogel with drug-loaded nanoparticles. Furthermore, the interaction between cells-matrix should be enhanced. All of these methods in combination with 3D cryoprinting. Additionally, the size of injectable hydrogels could be a barrier when moving from preclinical studies into clinical practice, where larger scaffolds are often required for humans. In the future, designing more compressible or self-healing injectable intelligent hydrogels should broaden their biomedical applications and accelerate their clinical translatability.

Other technology

Currently, various technologies, especially multifunctional systems (including photothermal therapy (PTT), layer-by-layer (LBL) self-assembly technique and 3D-printing technology), are widely used in diabetic wound repair.^{248–251}

Photothermal Therapy

PTT is based on near infrared (NIR) laser triggered therapy, widely used in cancer treatment. It combines near-infrared laser and light-absorbing nanomaterials to achieve local high temperature around NPs, leading to cancer cell death. Huang et al synthesized BSA-CuS nanoparticles by biomimetic mineralization method of bovine serum albumin (BSA) and copper sulfide (CuS), it showed strong killing bacterial ability under NIR.^{213,252} PB@PDA@Ag NPs can accelerate the healing of diabetic wounds under NIR.¹⁵⁰ In addition, MoS₂-BNN6 can effectively inhibit the growth of ampicillin-resistant *Escherichia coli*, heat-resistant *Escherichia faecalis*, and pathogen *Staphylococcus aureus*.²¹² Although nanoparticles based PTT has great potential for treating diabetic wound infections, local heat can also severely damage surrounding healthy tissue, so precise research and specific clinical trials are needed for PTT therapy.

Layer-by-Layer Self-Assembly Technique

Some biomaterials can improve their biomedical properties through many simple methods, such as layer-by-layer (LBL) self-assembly technique.²⁵³ LBL self-assembly technique is widely used in biomedical for delivery from a broad range of material surfaces.²⁵⁴ And LBL modified composite material has good stability, mechanical properties and hydrophilicity.^{255,256} LBL self-assembly technique is favored by many people because it can alternately deposit the electrostatic force with opposite charge on the surface of polyelectrolyte matrix, improving the continuous release of drugs, and is easy to operate, controllable and economical without potential complications.²⁵⁷ Natural rubber latex (NRL) can be used to treat chronic skin wounds, but because of their low integration, most applications of NRL biomembranes are external, short-term implants, or as delivery matrices.^{258,259} Davi et al can increase the membrane formation speed by 10 times by spraying LBL technology.²⁶⁰ In addition, self-assembled nanometer-scale coatings can incorporate and release therapeutically relevant quantities of siRNA in a controlled fashion to yield rapid diabetic wound closure⁷⁹ (Figure 8A and B). Thus, the use of LBL to alter localized protein expression levels has significant implications for the treatment of site-specific diseases, including cardiovascular disease, DFUs, cancers, and transplant rejection.

3D-Printed

3D-printed scaffolds for wound dressings have many advantages, such as the ability to adjust the dimensional characteristics of wound dressings (such as area, thickness, or pore size), simple drug loading, the use of a variety of materials, and oxygen penetration due to pore design.²⁶¹ Sodium alginate/polyethylene glycol (SA/PEG) scaffolds were prepared by adding different concentrations (1, 3 and 5 wt.%) of PEG to SA using 3D-printing technology. 3D-printing scaffolds had good antibacterial effect, especially against gram-positive bacteria. In addition, using 3D-printing technology, ideal porosity and properties were obtained, enabling cells to grow on/within the scaffold.²⁶² Wu et al used extrusion-based 3D printing and post stretching to fabricate a microneedle patch system for minimally invasive and glucose-responsive insulin delivery for diabetes treatment.²⁶³

Figure 9 Potential therapies for diabetic wound repair. Strategies for manipulating the regeneration of diabetic wounds include the use of hydrogels (loaded with small molecules and stem cells, etc.), photothermal therapy, and materials that release oxygen. All of these elements have been demonstrated to have an effect on in vitro and in vivo models of wound healing. These repair mechanisms include vascularization, less ROS production, oxygen release, and antimicrobial resistance. Therefore, combining these strategies will undoubtedly change the result of diabetic wound healing.

Conclusions and Perspectives

The treatment of diabetic wounds is complex and challenging due to its pathophysiology, resulting in impaired function of different cells and in unbalanced levels of key biochemical healing mediators. Based on the characteristics of diabetic wounds and the mechanism of tissue repair, nanoparticles/hydrogels loaded with bioactive molecules (such as growth factors, genes, proteins/peptides, stem cells/exosomes) and non-bioactive substances (metal ions, oxygen and nitric oxide), as well as nanotechnology (eg, PTT, LBL self-assembly technique and 3D printing) have been applied to diabetic wound healing (Figure 9). The etiopathogenesis of diabetic ulcers is too complex, one or two substances are not enough to accelerate wound healing, so a variety of substances can be combined to release in different stages of wounds to accelerate diabetic wound healing. Overall, the future direction may be the development of new biomaterials with multiple roles (including improve hypoxia, enhance angiogenesis, reduce oxidative stress and prevent infection) that may regulate wound healing at all stages and provide a balanced environment throughout the wound healing process, thereby reducing potential complications.

In recent years, people are interested in using various technologies to prepare some multifunctional nano-systems for diabetic wound healing. However, enough information about the physicochemical properties of nanoscale systems and their expected behavior and toxicity in human body remains unclear. In the long term, further studies are indispensable to provide insights into how research findings about technology-based therapies can be applied in the clinical arena. In the future, we are sure to design exciting intelligent nanotechnology platforms for the diagnosis and treatment of various chronic diseases.

Abbreviations

IL-6, Interleukin 6; TGF- β 1, Transforming growth factor- β 1; NGF, Nerve growth factor; KGF, Keratinocyte growth factor; VEGF, Vascular endothelial growth factor; IGF-1, Insulin-like growth factor; bFGF, basic Fibroblast growth factors b; AGE, Advanced glycation end-product; GF, Growth factor; LBL, Layer-by-layer; NO, Nitric oxide; NOS, Nitric oxide synthase; ECM, Extracellular matrix; MMP, Matrix metalloproteinases; TIMP, Tissue inhibitors of metalloproteinases; TNF α , Tumour necrosis factor α ;

GAG, Glycosaminoglycan; SDF-1, Stromal cell-derived factor 1; MIP-3 α , Macrophage inflammatory protein-3 α ; DFO, Desferrioxamine; PB, Prussian blue; NP, Nanoparticle; ADSCs, Adipose derived stem cells; GSH, Reduced glutathione; PTT, Photothermal therapy; HIF-1 α , Hypoxia-inducible factor 1 α ; M Φ , Macrophages; MRSA, Methicillin-resistant staphylococcus aureus; BG, Bioglass; nano-PFC, Nanoperfluorocarbon.

Acknowledgments

We acknowledge funding by the Innovation Capability Support Program of Shanxi (Program No. 2020TD-042), Jointly funded by Department of Science and Technology of Shaanxi Province and Northwestern Polytechnical University (No. 2020GXLH-Z-021), the National Natural Science Foundation of China (No. 81803491), the Natural Science Foundation of Shaanxi Province (No. 2019JQ-320), and the Fundamental Research Funds for the Central Universities (No. 3102019smxy002). We would like to thank the Analytical & Testing Center of Northwestern Polytechnical University for supporting our research on diabetic wound repair materials.

Disclosure

The authors declare that there are no competing interests.

References

- Shaw JE, Sicree RA, Zimmet PZ. Global estimates of the prevalence of diabetes for 2010 and 2030. *Diabetes Res Clin Pract*. 2010;87:4–14. doi:10.1016/j.diabres.2009.10.007
- Wang X, Sng MK, Foo S, et al. Early controlled release of peroxisome proliferator-activated receptor beta/delta agonist GW501516 improves diabetic wound healing through redox modulation of wound microenvironment. *J Control Release*. 2015;197:138–147. doi:10.1016/j.jconrel.2014.11.001
- Ahmed N. Advanced glycation endproducts—role in pathology of diabetic complications. *Diabetes Res Clin Pract*. 2005;67:3–21. doi:10.1016/j.diabres.2004.09.004
- McCance DR. Pregnancy and diabetes. *Best Pract Res Clin Endocrinol Metab*. 2011;25:945–958. doi:10.1016/j.beem.2011.07.009
- Mohammedi K, Maimaitiming S, Emery N, et al. Allelic variations in superoxide dismutase-1 (SOD1) gene are associated with increased risk of diabetic nephropathy in type 1 diabetic subjects. *Mol Genet Metab*. 2011;104(4):654–660. doi:10.1016/j.ymgme.2011.08.033
- Zhang S, Zhang Y, Wei X, et al. Expression and regulation of a novel identified TNFAIP8 family is associated with diabetic nephropathy. *BBA Mol Basis Dis*. 2010;1802:1078–1086. doi:10.1016/j.bbdis.2010.08.003
- Kim BY, Kim CH, Jung CH, et al. Association between subclinical hypothyroidism and severe diabetic retinopathy in Korean patients with type 2 diabetes. *Endocr J*. 2011;58:1065–1070. doi:10.1507/endocrj.EJ11-0281
- Silva L, Carvalho E, Cruz MT. Role of neuropeptides in skin inflammation and its involvement in diabetic wound healing. *Expert Opin Biol Ther*. 2010;10:1427–1439. doi:10.1517/14712598.2010.515207
- Kim SK, Lee KJ, Hahm JR, et al. Clinical significance of the presence of autonomic and vestibular dysfunction in diabetic patients with peripheral neuropathy. *Diab Metab J*. 2012;36:64–69. doi:10.4093/dmj.2012.36.1.64
- Sunkari VG, Lind F, Botusan IR, et al. Hyperbaric oxygen therapy activates hypoxia-inducible factor 1 (HIF-1), which contributes to improved wound healing in diabetic mice. *Wound Repair Regen*. 2015;23:98–103. doi:10.1111/wrr.12253
- Zamboni F, Collins MN. Cell based therapeutics in type 1 diabetes mellitus. *Int J Pharm*. 2017;521(1–2):346–356. doi:10.1016/j.ijpharm.2017.02.063
- Cahill D, Zamboni F, Collins MN. Radiological advances in pancreatic islet transplantation. *Acad Radiol*. 2019;26:1536–1543. doi:10.1016/j.acra.2019.01.006
- Sun YX, Shi H, Yin SQ, et al. Human mesenchymal stem cell derived exosomes alleviate type 2 diabetes mellitus by reversing peripheral insulin resistance and relieving β -cell destruction. *ACS Nano*. 2018;12:7613–7628. doi:10.1021/acsnano.7b07643
- Patel P, Macerollo A. Diabetes mellitus: diagnosis and screening. *Diabetes*. 2010;107:213–240. doi:10.3238/arztebl.2010.0231
- Vijayakumar V, Samal SK, Mohanty S, et al. Recent advancements in biopolymer and metal nanoparticle-based materials in diabetic wound healing management. *Int J Biol Macromol*. 2019;122:137–148. doi:10.1016/j.ijbiomac.2018.10.120
- Gurtner GC, Werner S, Barrandon Y, et al. Wound repair and regeneration. *Nature*. 2008;453:314–321. doi:10.1038/nature07039
- Schreml S, Szeimies RM, Prantl L, et al. Oxygen in acute and chronic wound healing. *Br J Dermatol*. 2010;1–12. doi:10.1111/j.1365-2133.2010.09804.x
- Broughton GII, Janis JE, Attinger CE. Wound healing: an overview. *Plast Reconstr Surg*. 2006;117:1e-S-32e-S. doi:10.1097/01.prs.0000222562.60260.f9
- Robson MC, Steed DL, Franz MG. Wound healing: biologic features and approaches to maximize healing trajectories. *Curr Probl Surg*. 2016;38(2):72–140. doi:10.1067/msg.2001.111167
- Chellappan DK, Yenese Y, Wei CC, et al. Nanotechnology and diabetic wound healing: a review. *Endocr Metab Immune Disord Drug Targets*. 2017;17:87–95. doi:10.2174/1871530317666170421121202
- Falanga V. Wound healing and its impairment in the diabetic foot. *Lancet*. 2005;366:1736–1743. doi:10.1007/978-1-62703-505-7_6
- Delavary BM, Veer WMVD, Egmond MV, et al. Macrophages in skin injury and repair. *Immunobiology*. 2011;216(7):753–762. doi:10.1016/j.imbio.2011.01.001
- Martin P, Leibovich SJ. Inflammatory cells during wound repair: the good, the bad and the ugly. *Trends Cell Biol*. 2005;15(11):599–607. doi:10.1016/j.tcb.2005.09.002
- Guo SA, DiPietro LA. Factors affecting wound healing. *J Dent Res*. 2010;89(3):219–229. doi:10.1177/0022034509359125
- O'Toole EA. Extracellular matrix and keratinocyte migration. *Clin Exp Dermatol*. 2001;26(6):525–530. doi:10.1046/j.1365-2230.2001.00891.x
- Hinz B. Formation and function of the myofibroblast during tissue repair. *J Invest Dermatol*. 2007;127(3):526–537. doi:10.1038/sj.jid.5700613
- Reinke JM, Sorg H. Wound repair and regeneration. *Eur Surg Res*. 2012;49:35–43. doi:10.1159/000339613
- Gonzalez AC, Costa TF, Andrade ZA, et al. Wound healing – a literature review. *An Bras Dermatol*. 2016;91:614–620. doi:10.1590/abd1806-4841.20164741
- Lazarus GS, Cooper DM, Knighton DR, et al. Definitions and guidelines for assessment of wounds and evaluation of healing. *Wound Repair Regen*. 1994;2:165–170. doi:10.1046/j.1524-475X.1994.20305.x

30. Desmeta CM, Prat V, Gallez B. Nanomedicines and gene therapy for the delivery of growth factors to improve perfusion and oxygenation in wound healing. *Adv Drug Deliv Rev.* **2018**;129:262–284. doi:10.1016/j.addr.2018.02.001
31. Choudhury H, Pandey M, Lim YQ, et al. Silver nanoparticles: advanced and promising technology in diabetic wound therapy. *Mater Sci Eng C.* **2020**;112:11092. doi:10.1016/j.msec.2020.110925
32. Woo K, Ayello EA, Sibbald RG. The edge effect: current therapeutic options to advance the wound edge. *Adv Skin Wound Care.* **2007**;20:99–117. doi:10.1097/00129334-200702000-00009
33. Eming SA, Krieg T, Davidson JM. Inflammation in wound repair: molecular and cellular mechanisms. *J Invest Dermatol.* **2007**;127:514–525. doi:10.1038/sj.jid.5700701
34. Margadant C, Sonnenberg A. Integrin–TGF- β crosstalk in fibrosis, cancer and wound healing. *EMBO Reports.* **2010**;11(2):97–105. doi:10.1038/embor.2009.276
35. Yang L, Zheng Z, Zhou Q, et al. miR-155 promotes cutaneous wound healing through enhanced keratinocytes migration by MMP-2. *J Mol Histol.* **2017**;48:147–155. doi:10.1007/s10735-017-9713-8
36. Prabhakar PK, Singh K, Kabra D, et al. Natural SIRT1 modifiers as promising therapeutic agents for improving diabetic wound healing. *Phytomedicine.* **2020**;76:153252. doi:10.1016/j.phymed.2020.153252
37. Thangarajah H, Yao D, Chang EI, et al. The molecular basis for impaired hypoxia-induced VEGF expression in diabetic tissues. *PNAS.* **2009**;106:13505–13510. doi:10.1073/pnas.0906670106
38. Schaper NC, Van Netten JJ, Apelqvist J, et al. Prevention and management of foot problems in diabetes: a summary guidance for daily practice 2015, based on the IWGDF guidance documents. *Diabetes/Metab Res Rev.* **2016**;32:7–15. doi:10.1016/j.diabres.2016.12.007
39. Ezhilarasu H, Vishalli D, Dheen ST, et al. Nanoparticle-based therapeutic approach for diabetic wound healing. *Nanomaterials.* **2020**;10:1234. doi:10.3390/nano10061234
40. Chen L, Zheng Q, Liu YP, et al. Adipose-derived stem cells promote diabetic wound healing via the recruitment and differentiation of endothelial progenitor cells into endothelial cells mediated by the VEGF-PLC gamma-ERK pathway. *Arch Biochem Biophys.* **2020**;692:108531. doi:10.1016/j.abb.2020.108531
41. Armstrong DG, Boulton AJ, Bus SA. Diabetic foot ulcers and their recurrence. *N Engl J Med.* **2017**;376:2367–2375. doi:10.1056/NEJMr1615439
42. Dinh T, Tecilazich F, Kafanas A, et al. Mechanisms involved in the development and healing of diabetic foot ulceration. *Diabetes.* **2012**;61:2937–2947. doi:10.2337/db12-0227
43. Charo IF, Ransohoff RM. The many roles of chemokines and chemokine receptors in inflammation. *N Engl J Med.* **2006**;354:610–621. doi:10.1056/NEJMr052723
44. Rosenkilde MM, Schwartz TW. The chemokine system – a major regulator of angiogenesis in health and disease. *APMIS.* **2004**;112:481–495. doi:10.1111/j.1600-0463.2004.apm11207-0808.x
45. Jiang BC, Liu T, Gao YJ. Chemokines in chronic pain: cellular and molecular mechanisms and therapeutic potential. *Pharmacol Ther.* **2020**;212:107581. doi:10.1016/j.pharmthera.2020.107581
46. Peppas NA, Hilt JZ, Khademhosseini A, et al. Hydrogels in biology and medicine: from molecular principles to bionanotechnology. *Adv Mater.* **2006**;18(11):1345–1360. doi:10.1002/adma.200501612
47. Chai QY, Jiao Y, Yu XJ. Hydrogels for biomedical applications: their characteristics and the mechanisms behind them. *Gels.* **2017**;3(1):6. doi:10.3390/gels3010006
48. Lee Y, Bae JW, Lee JW, et al. Enzyme-catalyzed in situ forming gelatin hydrogels as bioactive wound dressings: effects of fibroblast delivery on wound healing efficacy. *J Mater Chem B.* **2014**;2:7712–7718. doi:10.1039/c4tb01111b
49. Lee SH, Lee Y, Chun YW, et al. In situ crosslinkable gelatin hydrogels for vasculogenic induction and delivery of mesenchymal stem cells. *Adv Funct Mater.* **2014**;24:6771–6781. doi:10.1002/adfm.201401110
50. Dong SY, Lee YK, Ryu HA, et al. Cell recruiting chemokine-loaded sprayable gelatin hydrogel dressings for diabetic wound healing. *Acta Biomater.* **2016**;38:59–68. doi:10.1016/j.actbio.2016.04.030
51. Greenhalgh DG. The role of growth factors in wound healing. *J Trauma.* **1996**;41:159–167. doi:10.1097/00005373-199607000-00029
52. Badillo AT, Chung S, Zhang L, et al. Lentiviral gene transfer of SDF-1alpha to wounds improves diabetic wound healing. *J Surg Res.* **2007**;143:35–42. doi:10.1016/j.jss.2007.03.051
53. Gainza G, Villullas S, Pedraz JL, et al. Advances in drug delivery systems (DDSs) to release growth factors for wound healing and skin regeneration. *Nanomedicine.* **2015**;11:1551–1573. doi:10.1016/j.nano.2015.03.002
54. Rui L, Yiyang L, Yanqing W, et al. Heparin-polyoxamer thermosensitive hydrogel loaded with bFGF and NGF enhances peripheral nerve regeneration in diabetic rats. *Biomaterials.* **2018**;168:24–37. doi:10.1016/j.biomaterials.2018.03.044
55. Zhu Y, Hoshi R, Chen S, et al. Sustained release of stromal cell derived factor-1 from an antioxidant thermoresponsive hydrogel enhances dermal wound healing in diabetes. *J Control Release.* **2016**;238:114–122. doi:10.1016/j.jconrel.2016.07.043
56. Chereddy KK, Lopes A, Koussoroplis S, et al. Combined effects of PLGA and vascular endothelial growth factor promote the healing of non-diabetic and diabetic wounds. *Nanomedicine: NBM.* **2015**;11:1975–1984. doi:10.1016/j.nano.2015.07.006
57. Hui Q, Zhang L, Yang XX, et al. Higher biostability of rh-aFGF-carbomer 940 hydrogel and its effect on wound healing in a diabetic rat model. *ACS Biomater Sci Eng.* **2018**;4:1661–1668. doi:10.1021/acsbiomaterials.8b00011
58. Losi P, Briganti E, Errico C, et al. Fibrin-based scaffold incorporating VEGF- and bFGF-loaded nanoparticles stimulates wound healing in diabetic mice. *Acta Biomater.* **2013**;9:7814–7821. doi:10.1016/j.actbio.2013.04.019
59. Lai HJ, Kuan CH, Wu HC, et al. Tailor design electrospun composite nanofibers with staged release of multiple angiogenic growth factors for chronic wound healing. *Acta Biomater.* **2014**;10:4156–4166. doi:10.1016/j.actbio.2014.05.001
60. Lee CH, Liu KS, Cheng CW, et al. Co-delivery of sustainable anti-microbial agents and platelet-derived growth factor via biodegradable nanofibers for repair of diabetic infectious wounds. *ACS Infect Dis.* **2020**. doi:10.1021/acsinfecdis.0c00321
61. Zhu JY, Jiang GH, Hong WJ, et al. Rapid gelation of oxidized hyaluronic acid and succinyl chitosan for integration with insulin-loaded micelles and epidermal growth factor on diabetic wound healing. *Mater Sci Eng C.* **2020**;117:111273. doi:10.1016/j.msec.2020.111273
62. Nissen NN, Polverini PJ, Koch AE, et al. Vascular endothelial growth factor mediates angiogenic activity during the proliferative phase of wound healing. *Am J Pathol.* **1998**;152:1445–1452. doi:10.1097/00000433-199806000-00022
63. Brown LF, Yeo KT, Berse B, et al. Expression of vascular permeability factor (vascular endothelial growth factor) by epidermal keratinocytes during wound healing. *J Exp Med.* **1992**;176:1375–1379. doi:10.1084/jem.176.5.1375
64. Peters KG, De Vries C, Williams LT. Vascular endothelial growth factor receptor expression during embryogenesis and tissue repair suggests a role in endothelial differentiation and blood vessel growth. *Proc Natl Acad Sci.* **1993**;90:8915–8919. doi:10.1073/pnas.90.19.8915
65. Galiano RD, Tepper OM, Pelo CR, et al. Topical vascular endothelial growth factor accelerates diabetic wound healing through increased angiogenesis and by mobilizing and recruiting bone marrow-derived cells. *Am J Pathol.* **2004**;164:1935–1947. doi:10.1016/S0002-9440(10)63754-6

66. Guo R, Xu S, Ma L, et al. Enhanced angiogenesis of gene-activated dermal equivalent for treatment of full thickness incisional wounds in a porcine model. *Biomaterials*. 2010;31:7308–7320. doi:10.1016/j.biomaterials.2010.06.013
67. Guo R, Xu S, Ma L, et al. The healing of full-thickness burns treated by using plasmid DNA encoding VEGF-165 activated collagen-chitosan dermal equivalents. *Biomaterials*. 2011;32:1019–1031. doi:10.1016/j.biomaterials.2010.08.087
68. Tokatlian T, Cam C, Segura T. Non-viral DNA delivery from porous hyaluronic acid hydrogels in mice. *Biomaterials*. 2014;35:825–835. doi:10.1016/j.biomaterials.2013.10.014
69. Prestwich GD. Clinical biomaterials for scar-free healing and localized delivery of cells and growth factors. *Adv Wound Care*. 2010;1:394–399. doi:10.1089/awc.2009.0124
70. Tokatlian T, Cam C, Segura T. Porous hyaluronic acid hydrogels for localized nonviral DNA delivery in a diabetic wound healing model. *Adv Healthcare Mater*. 2015;4:1084–1091. doi:10.1002/adhm.201400783
71. Devalliere J, Dooley K, Hu Y, et al. Co-delivery of a growth factor and a tissue-protective molecule using elastin biopolymers accelerates wound healing in diabetic mice. *Biomaterials*. 2017;141:149–160. doi:10.1016/j.biomaterials.2017.06.043
72. Kempen DHR, Lu L, Heijink A, et al. Effect of local sequential VEGF and BMP-2 delivery on ectopic and orthotopic bone regeneration. *Biomaterials*. 2009;30:2816–2825. doi:10.1016/j.biomaterials.2009.01.031
73. Roberts JJ, Farrugia BL, Green RA, et al. In situ formation of poly (vinyl alcohol)-heparin hydrogels for mild encapsulation and prolonged release of basic fibroblast growth factor and vascular endothelial growth factor. *J Tissue Eng*. 2016;7:1–10. doi:10.1177/2041731416677132
74. Kano MR, Morishita Y, Iwata C, et al. VEGF-A and FGF-2 synergistically promote neoangiogenesis through enhancement of endogenous PDGF-B-PDGFβ signaling. *J Cell Sci*. 2005;118:3759–3768. doi:10.1242/jcs.02483
75. Jiang X, Lin H, Jiang D, et al. Co-delivery of VEGF and bFGF via a PLGA nanoparticle-modified BAM for effective contracture inhibition of regenerated bladder tissue in rabbits. *Sci Rep*. 2016;6:20784. doi:10.1038/srep20784
76. Icli B, Nabzyk CS, Lujan-Hernandez J, et al. Regulation of impaired angiogenesis in diabetic dermal wound healing by microRNA-26a. *J Mol Cell Cardiol*. 2016;91:151–159. doi:10.1016/j.yjmcc.2016.01.007
77. Wu H, Li F, Shao W, et al. Promoting angiogenesis in oxidative diabetic wound microenvironment using a nanozyme-reinforced self-protecting hydrogel. *ACS Cent Sci*. 2019;5:477–485. doi:10.1021/acscentsci.8b00850
78. Li N, Luo HC, Ren M, et al. Efficiency and safety of β-CD-(D₃)₇ as siRNA carrier for decreasing matrix metalloproteinase-9 expression and improving wound healing in diabetic rats. *ACS Appl Mater Interfaces*. 2017;9:17417–17426. doi:10.1021/acsami.7b02809
79. Castleberry SA, Almquist BD, Li W, et al. Self-assembled wound dressings silence MMP-9 and improve diabetic wound healing in vivo. *Adv Mater*. 2016;28:1809–1817. doi:10.1002/adma.201503565
80. Lou D, Luo Y, Pang Q, et al. Gene-activated dermal equivalents to accelerate healing of diabetic chronic wounds by regulating inflammation and promoting angiogenesis. *Bioact Mater*. 2020;5:667–679. doi:10.1016/j.bioactmat.2020.04.018
81. Rabbani PS, Zhou A, Borab ZM, et al. Novel lipoproteoplex delivers Keap1 siRNA based gene therapy to accelerate diabetic wound healing. *Biomaterials*. 2017;132:1–15. doi:10.1016/j.biomaterials.2017.04.001
82. Turner N, Grose R. Fibroblast growth factor signalling: from development to cancer. *Nat Rev Cancer*. 2010;10:116–129. doi:10.1038/nrc2780
83. Chen J, Wu C, Oupicky D. Bio-reducible hyperbranched poly(amido amine)s for gene delivery. *Biomacromolecules*. 2009;10:2921–2927. doi:10.1021/bm900724c
84. Senturk B, Mercan S, Delibas T, et al. Angiogenic peptide nanofibers improve wound healing in STZ-induced diabetic rats. *ACS Biomater Sci Eng*. 2016;2:1180–1189. doi:10.1021/acsbomaterials.6b00238
85. Wang JH, Chen XY, Zhao Y, et al. pH-switchable antimicrobial nanofiber networks of hydrogel eradicate biofilm and rescue stalled healing in chronic wounds. *ACS NANO*. 2019;10:11686–11697. doi:10.1021/acsnano.9b05608
86. Zhang QK, Oh JH, Park CH, et al. Effects of dimethylolallylglycine-embedded poly(ε-caprolactone) fiber meshes on wound healing in diabetic rats. *ACS Appl Mater Interfaces*. 2017;9:7950–7963. doi:10.1021/acsami.6b15815
87. Cifuentes A, Gomez-Gil V, Ortega MA, et al. Chitosan hydrogels functionalized with either unfractionated heparin or bemiparin improve diabetic wound healing. *Biomed Pharmacother*. 2020;129:110498. doi:10.1016/j.biopha.2020.110498
88. Lin SY, Zhang Q, Li SH, et al. Antioxidative and angiogenesis-promoting effects of tetrahedral framework nucleic acids in diabetic wound healing with activation of the Akt/Nrf2/HO-1 pathway. *ACS Appl Mater Interfaces*. 2020;12:11397–11408. doi:10.1021/acsami.0c00874
89. Chen SX, Zhang M, Shao XB, et al. Laminin mimetic peptide SIKVAV-chitosan hydrogel promoting wound healing by enhancing angiogenesis, re-epithelialization and collagen deposition. *J Mater Chem B*. 2015;3:6798–6804. doi:10.1039/c5tb00842e
90. Peng ZH, Nguyen TT, Song W, et al. Selective MMP-9 inhibitor (R)-ND-336 alone or in combination with linezolid accelerates wound healing in infected diabetic mice. *ACS Pharmacol Transl Sci*. 2020. doi:10.1021/acspstsci.0c00104
91. Carrejo NC, Moore AN, Silva TLL, et al. Hartgerink, multidomain peptide hydrogel accelerates healing of full-thickness wounds in diabetic mice. *ACS Biomater Sci Eng*. 2018;4:1386–1396. doi:10.1021/acsbomaterials.8b00031
92. Yang HS, Lai C, Xuan CK, et al. Integrin-binding pro-survival peptide engineered silk fibroin nanosheets for diabetic wound healing and skin regeneration. *Chem Eng J*. 2020;398:125617. doi:10.1016/j.cej.2020.125617
93. Chouhan D, Das P, Thatikonda N, et al. Silkworm silk matrices coated with functionalized spider silk accelerate healing of diabetic wounds. *ACS Biomater Sci Eng*. 2019;5:3537–3548. doi:10.1021/acsbomaterials.9b00514
94. Mizuno H, Tobita M, Uysal AC. Concise review: adipose-derived stem cells as a novel tool for future regenerative medicine. *Stem Cells*. 2012;30:804–810. doi:10.1002/stem.1076
95. Dong YX, Rodrigues M, Kwon SH, et al. Acceleration of diabetic wound regeneration using an in situ-formed stem-cell-based skin substitute. *Adv Healthcare Mater*. 2018;7:1800432. doi:10.1002/adhm.201800432
96. Fu JP, Zhang Y, Chu J, et al. Reduced graphene oxide incorporated acellular dermal composite scaffold enables efficient local delivery of mesenchymal stem cells for accelerating diabetic wound healing. *ACS Biomater Sci Eng*. 2019;5:4054–4066. doi:10.1021/acsbomaterials.9b00485
97. Liu S, Yu J, Zhang QF, et al. Dual cross-linked HHA hydrogel supplies and regulates MΦ2 for synergistic improvement of immunocompromise and impaired angiogenesis to enhance diabetic chronic wound healing. *Biomacromolecules*. 2020;21:3795–3806. doi:10.1021/acs.biomac.0c00891
98. Tyeb S, Shiekh PA, Verma V, et al. Adipose-derived stem cells (ADSCs) loaded gelatin-sericin-laminin cryogels for tissue regeneration in diabetic wounds. *Biomacromolecules*. 2020;21:294–304. doi:10.1021/acs.biomac.9b01355

99. Gao WD, Jin WW, Li YN, et al. A highly bioactive bone extracellular matrix-biomimetic nanofibrous system with rapid angiogenesis promotes diabetic wound healing. *J Mater Chem B*. 2017;5:7285–7296. doi:10.1039/c7tb01484h
100. Morris AH, Lee H, Xing H, et al. Tunable hydrogels derived from genetically engineered extracellular matrix accelerate diabetic wound healing. *ACS Appl Mater Interfaces*. 2018;10:41892–41901. doi:10.1021/acsami.8b08920
101. Morris AH, Stamer DK, Kunkemoeller B, et al. Decellularized materials derived from TSP2-KO mice promote enhanced neovascularization and integration in diabetic wounds. *Biomaterials*. 2018;169:61–71. doi:10.1016/j.biomaterials.2018.03.049
102. Wang H, Agarwal P, Xiao Y, et al. A nano-in-micro system for enhanced stem cell therapy of ischemic diseases. *ACS Cent Sci*. 2017;3:875–885. doi:10.1021/acscentsci.7b00213
103. Shen YI, Cho H, Papa AE, et al. Engineered human vascularized constructs accelerate diabetic wound healing. *Biomaterials*. 2016;102:107–119. doi:10.1016/j.biomaterials.2016.06.009
104. Shi Q, Qian Z, Liu D, et al. GMSC-derived exosomes combined with a chitosan/silk hydrogel sponge accelerates wound healing in a diabetic rat skin defect model. *Front Physiol*. 2017;8:904. doi:10.3389/fphys.2017.00904
105. Johnstone RM, Adam M, Hammond JR, et al. Vesicle formation during reticulocyte maturation. Association of plasma membrane activities with released vesicles (exosomes). *J Biol Chem*. 1987;262:9412–9420. doi:10.1557/PROC-0928-GG08-04
106. de Gassart A, Geminard C, Fevrier B, et al. Lipid raft-associated protein sorting in exosomes. *Blood*. 2003;102:4336–4344. doi:10.1182/blood-2003-03-0871
107. Wubbolts R, Leckie RS, Veenhuizen PT, et al. Proteomic and biochemical analyses of human B cell-derived exosomes, potential implications for their function and multivesicular body formation. *J Biol Chem*. 2003;278:10963–10972. doi:10.1074/jbc.M207550200
108. Lai RC, Yeo RW, Lim SK. Mesenchymal stem cell exosomes. *Semin Cell Dev Biol*. 2015;40:82–88. doi:10.1016/j.semdb.2015.03.001
109. Haney MJ, Klyachko NL, Zhao Y, et al. Exosomes as drug delivery vehicles for Parkinson's disease therapy. *J Control Release*. 2015;207:18–30. doi:10.1016/j.jconrel.2015.03.033
110. Batrakova EV, Kim MS. Using exosomes, naturally-equipped nano-carriers, for drug delivery. *J Control Release*. 2015;219:396–405. doi:10.1016/j.jconrel.2015.07.030
111. Shtam TA, Kovalev RA, Varfolomeeva EY, et al. Exosomes are natural carriers of exogenous siRNA to human cells in vitro. *Cell Commun Signal*. 2013;11:88. doi:10.1186/1478-811X-11-88
112. Li X, Chen C, Wei L, et al. Exosomes derived from endothelial progenitor cells attenuate vascular repair and accelerate reendothelialization by enhancing endothelial function. *Cytotherapy*. 2016;18:253–262. doi:10.1016/j.jcyt.2015.11.009
113. Rani S, Ritter T. The exosome – a naturally secreted nanoparticle and its application to wound healing. *Adv Mater*. 2016;28:5542–5552. doi:10.1002/adma.201504009
114. Yu MY, Liu W, Li JX, et al. Exosomes derived from atorvastatin-pretreated MSC accelerate diabetic wound repair by enhancing angiogenesis via AKT/eNOS pathway. *Stem Cell Res Ther*. 2020;1:350. doi:10.1186/s13287-020-01824-2
115. Lv QJ, Deng JF, Chen Y, et al. Engineered human adipose stem-cell-derived exosomes loaded with miR-21-5p to promote diabetic cutaneous wound healing. *Mol Pharm*. 2020;17:1723–1733. doi:10.1021/acs.molpharmaceut.0c00177
116. Wang CG, Wang M, Xu TZ, et al. Engineering bioactive self-healing antibacterial exosomes hydrogel for promoting chronic diabetic wound healing and complete skin regeneration. *Theranostics*. 2019;9(1):65–76. doi:10.7150/thno.29766
117. Wang M, Wang CG, Chen M, et al. Efficient angiogenesis-based diabetic wound healing/skin reconstruction through bioactive antibacterial adhesive ultraviolet shielding nanodressing with exosome release. *ACS Nano*. 2019;13:10279–10293. doi:10.1021/acsnano.9b03656
118. Tao SC, Guo SC, Min L, et al. Chitosan wound dressings incorporating exosomes derived from microRNA-126-overexpressing synovium mesenchymal stem cells provide sustained release of exosomes and heal full-thickness skin defects in a diabetic rat model. *Stem Cells Transl Med*. 2017;6:736–747. doi:10.5966/sctm.2016-0275
119. Li M, Ke QF, Tao SC, et al. Fabrication of hydroxyapatite/chitosan composite hydrogels loaded with exosomes derived from miR-126-3p overexpressed synovium mesenchymal stem cells for diabetic chronic wound healing. *J Name*. 2013;1–11. doi:10.1039/C6TB01560C
120. Jyoti K, Malik G, Chaudhary M, et al. Chitosan and phospholipid assisted topical fusidic acid drug delivery in burn wound: strategies to conquer pharmaceutical and clinical challenges, opportunities and future panorama. *Int J Biol Macromol*. 2020;161:325–335. doi:10.1016/j.ijbiomac.2020.05.230
121. Yang Y, Yin DK, Wang F, et al. In situ eNOS/NO up-regulation – a simple and effective therapeutic strategy for diabetic skin ulcer. *Sci Rep*. 2016;6:30326. doi:10.1038/srep30326
122. Amiel AG, Durand CP, Maton M, et al. Designed sponges based on chitosan and cyclodextrin polymer for a local release of ciprofloxacin in diabetic foot infections. *Int J Pharm*. 2020;587:119677. doi:10.1016/j.ijpharm.2020.119677
123. Wu YB, Zhou ZP, Luo L, et al. A non-anticoagulant heparin-like snail glycosaminoglycan promotes healing of diabetic wound. *Carbohydr Polym*. 2020;247:116682. doi:10.1016/j.carbpol.2020.116682
124. Ren J, Yang MJ, Chen JW, et al. Anti-inflammatory and wound healing potential of kirenol in diabetic rats through the suppression of inflammatory markers and matrix metalloproteinase expressions. *Biomed Pharmacother*. 2020;129:110475. doi:10.1016/j.biopha.2020.110475
125. Chu J, Shi PP, Yan WX, et al. PEGylated graphene oxide-mediated quercetin-modified collagen hybrid scaffold for enhancement of MSCs differentiation potential and diabetic wound healing. *Nanoscale*. 2018;10:9547–9560. doi:10.1039/c8nr02538j
126. Mittal AK, Bhardwaj R, Arora R, et al. Acceleration of wound healing in diabetic rats through poly dimethylaminoethyl acrylate–hyaluronic acid polymeric hydrogel impregnated with a didymocarpus pedicellatus plant extract. *ACS Omega*. 2020. doi:10.1021/acsomega.0c02040
127. Liu YY, Sui YL, Liu C, et al. A physically crosslinked polydopamine/nanocellulose hydrogel as potential versatile vehicles for drug delivery and wound healing. *Carbohydrate Polymers*. 2018;188:27–36. doi:10.1016/j.carbpol.2018.01.093
128. Marti'nez-Romero R, Marti'nez-Lara E, Aguilar-Quesada R, et al. PARP-1 modulates deferoxamine-induced HIF-1 α accumulation through the regulation of nitric oxide and oxidative stress. *J Cell Biochem*. 2008;104:2248. doi:10.1002/jcb.21781
129. Wu Y, Li X, Xie W, et al. Neuroprotection of deferoxamine on rotenone-induced injury via accumulation of HIF-1 α and induction of autophagy in SH-SY5Y cells. *Neurochem Int*. 2010;57:198–205. doi:10.1016/j.neuint.2010.05.008
130. Hou ZJ, Nie CL, Si ZX, et al. Deferoxamine enhances neovascularization and accelerates wound healing in diabetic rats via the accumulation of hypoxia-inducible factor-1 α . *Diabetes Res Clin Pract*. 2013;101:62–71. doi:10.1016/j.diabetes.2013.04.012
131. Xing D, Liu L, Marti GP, et al. Hypoxia and hypoxia-inducible factor in the burn wound. *Wound Repair Regen*. 2011;19:205. doi:10.1111/j.1524-475X.2010.00656.x
132. Chen H, Jia P, Kang H, et al. Upregulating Hif-1 α by hydrogel nanofibrous scaffolds for rapidly recruiting angiogenesis relative cells in diabetic wound. *Adv Healthcare Mater*. 2016;5:907–918. doi:10.1002/adhm.201501018

133. Chen H, Guo L, Wicks J, et al. Quickly promoting angiogenesis by using a DFO-loaded photo-crosslinked gelatin hydrogel for diabetic skin regeneration. *J Mater Chem B*. 2016;4:3770–3781. doi:10.1039/c6tb00065g
134. Duschler D, Neofytou E, Wong VW, et al. Transdermal deferoxamine prevents pressure-induced diabetic ulcers. *PNAS*. 2015;112:94–99. doi:10.1073/pnas.1413445112
135. Kong L, Zhi W, Zhao H, et al. Bioactive injectable hydrogels containing desferrioxamine and bioglass for diabetic wound healing. *ACS Appl Mater Interfaces*. 2018;10:30103–30114. doi:10.1021/acsami.8b09191
136. Emanuelli T, Burgeiro A, Carvalho E. Effects of insulin on the skin: possible healing benefits for diabetic foot ulcers. *Arch Dermatol Res*. 2016;308:677–694. doi:10.1007/s00403-016-1686-z
137. Zhao LL, Niu LJ, Liang HZ, et al. pH and glucose dual-responsive injectable hydrogels with insulin and fibroblasts as bioactive dressings for diabetic wound healing. *ACS Appl Mater Interfaces*. 2017;9:37563–37574. doi:10.1021/acsami.7b09395
138. Ren XZ, Han YM, Wang J, et al. An aligned porous electrospun fibrous membrane with controlled drug delivery – an efficient strategy to accelerate diabetic wound healing with improved angiogenesis. *Acta Biomater*. 2018;70:140–153. doi:10.1016/j.actbio.2018.02.010
139. Liu J, Chen ZQ, Wang J, et al. Encapsulation of curcumin nanoparticles with MMP9-responsive and thermos-sensitive hydrogel improves diabetic wound healing. *ACS Appl Mater Interfaces*. 2018;10:16315–16326. doi:10.1021/acsami.8b03868
140. Ghufuran H, Mehmood A, Azam M, et al. Curcumin preconditioned human adipose derived stem cells co-transplanted with platelet rich plasma improve wound healing in diabetic rats. *Life Sci*. 2020;257:118091. doi:10.1016/j.lfs.2020.118091
141. Karri VVSR, Kuppusamy G, Talluri SV, et al. Curcumin loaded chitosan nanoparticles impregnated into collagen-alginate scaffolds for diabetic wound healing. *Int J Biol Macromol*. 2020;257:118091. doi:10.1016/j.ijbiomac.2016.05.038
142. Mendes C, Hauptenthal DPD, Zaccaron RP, et al. Effects of the association between photobiomodulation and hyaluronic acid linked gold nanoparticles in wound healing. *ACS Biomater Sci Eng*. 2020;6:5132–5144. doi:10.1021/acsbiomaterials.0c00294
143. Edwards JV, Prevost NT, Santiago M, et al. Hydrogen peroxide generation of copper/ascorbate formulations on cotton: effect on antibacterial and fibroblast activity for wound healing application. *Molecules*. 2018;23:2399. doi:10.3390/molecules23092399
144. Maity GN, Maity P, Choudhuri I, et al. Green synthesis, characterization, antimicrobial and cytotoxic effect of silver nanoparticles using arabinoxylan isolated from Kalmegh. *Int J Biol Macromol*. 2020;162:1025–1034. doi:10.1016/j.ijbiomac.2020.06.215
145. Mao CY, Xiang YM, Liu XM, et al. Photo-inspired antibacterial activity and wound healing acceleration by hydrogel embedded with Ag/Ag@AgCl/ZnO nanostructures. *ACS Nano*. 2017;11:9010–9021. doi:10.1021/acs.nano.7b03513
146. Shi LY, Zhao YN, Xie QF, et al. Moldable hyaluronan hydrogel enabled by dynamic metal–bisphosphonate coordination chemistry for wound healing. *Adv Healthcare Mater*. 2018;7:1700973. doi:10.1002/adhm.201700973
147. Zhang PJ, Li Y, Tang YH, et al. Copper-based metal–organic framework as a controllable nitric oxide-releasing vehicle for enhanced diabetic wound healing. *ACS Appl Mater Interfaces*. 2020;12:18319–18331. doi:10.1021/acsami.0c01792
148. Salomoni R, Léo P, Montemor AF, et al. Antibacterial effect of silver nanoparticles in *Pseudomonas aeruginosa*. *Nanotechnol Sci Appl*. 2017;10:115–121. doi:10.2147/NSA.S133415
149. Qiao Y, Fei M, Liu C, et al. Near-infrared laser-excited nanoparticles to eradicate multidrug-resistant bacteria and promote wound healing. *ACS Appl Mater Interfaces*. 2018;10(1):193–206. doi:10.1021/acsami.7b15251
150. Tong CY, Zhong XH, Yang YJ, et al. PB@PDA@Ag nanosystem for synergistically eradicating MRSA and accelerating diabetic wound healing assisted with laser irradiation. *Biomaterials*. 2020;243:119936. doi:10.1016/j.biomaterials.2020.119936
151. Zhao Y, Li ZH, Song SL, et al. Skin-inspired antibacterial conductive hydrogels for epidermal sensors and diabetic foot wound dressings. *Adv Funct Mater*. 2019;29:1901474. doi:10.1002/adfm.201901474
152. Pankhurst QA, Connolly J, Jones SK, et al. Applications of magnetic nanoparticles in biomedicine. *J Phys D Appl Phys*. 2003;36(13):167–181. doi:10.1088/0022-3727/36/13/201
153. Anker JN, Hall WP, Lyandres O, et al. Biosensing with plasmonic nanosensors. *Nat Mater*. 2008;7(6):442–453. doi:10.1038/nmat2162
154. Wrobel JS, Najafi B. Diabetic foot biomechanics and gait dysfunction. *J Diabetes Sci Technol*. 2010;4(4):833–845. doi:10.1177/193229681000400411
155. Pissuwan D, Valenzuela SM, Cortie MB. Therapeutic possibilities of plasmonically heated gold nanoparticles. *Trends Biotechnol*. 2006;24(2):62–67. doi:10.1016/j.tibtech.2005.12.004
156. Kim H, Kawazoe T, Han DW, et al. Enhanced wound healing by an epigallocatechin gallate-incorporated collagen sponge in diabetic mice. *Wound Repair Regen*. 2008;16(5):714–720. doi:10.1111/j.1524-475X.2008.00422.x
157. Leu J-G, Chen S-A, Chen H-M, et al. The effects of gold nanoparticles in wound healing with antioxidant epigallocatechin gallate and α -lipoic acid. *Nanomedicine*. 2012;8(5):767–775. doi:10.1016/j.nano.2011.08.013
158. Wang S, Yan C, Zhang XM, et al. Antimicrobial peptide modification enhances the gene delivery and bactericidal efficiency of gold nanoparticles for accelerating diabetic wound healing. *Biomater Sci*. 2018;6:2757–2772. doi:10.1039/c8bm00807h
159. Xiao JS, Zhu YX, Huddleston S, et al. Copper metal–organic framework nanoparticles stabilized with folic acid improve wound healing in diabetes. *ACS Nano*. 2018;12:1023–1032. doi:10.1021/acs.nano.7b01850
160. Xiao JS, Chen S, Yi J, et al. A cooperative copper metal–organic framework-hydrogel system improves wound healing in diabetes. *Adv Funct Mater*. 2017;27:1604872. doi:10.1002/adfm.201604872
161. Bhadauriya P, Mamtani H, Ashfaq M, et al. Synthesis of yeast-immobilized and copper nanoparticle-dispersed carbon nanofiber-based diabetic wound dressing material: simultaneous control of glucose and bacterial infections. *ACS Appl Bio Mater*. 2018;1:246–258. doi:10.1021/acsabm.8b00018
162. Lv F, Wang J, Xu P, et al. A conductive bioceramic/polymer composite biomaterial for diabetic wound healing. *Acta Biomater*. 2017;60:128–143. doi:10.1016/j.actbio.2017.07.020
163. Jiang YQ, Li Y, Li JK, et al. A mussel-inspired extracellular matrix-mimicking composite scaffold for diabetic wound healing. *ACS Appl Bio Mater*. 2020;3:4052–4061. doi:10.1021/acsabm.0c00143
164. Li JY, Lv F, Xu H, et al. A patterned nanocomposite membrane for high-efficiency healing of diabetic wound. *J Mater Chem B*. 2017;5:1926–1934. doi:10.1039/c7tb00124j
165. Das M, Goswami U, Kandimalla R, et al. Iron–copper bimetallic nanocomposite reinforced dressing materials for infection control and healing of diabetic wound. *ACS Appl Bio Mater*. 2019;2:5434–5445. doi:10.1021/acsabm.9b00870
166. Raucci MG, Demitri C, Soriente A, et al. Gelatin/nano-hydroxyapatite hydrogel scaffold prepared by sol-gel technology as filler to repair bone defects. *J Biomed Mater Res Part A*. 2018;106:2007–2019. doi:10.1002/jbm.a.36395
167. Xie WH, Fu XL, Tang FL, et al. Dose-dependent modulation effects of bioactive glass particles on macrophages and diabetic wound healing. *J Mater Chem B*. 2019;7:940. doi:10.1039/c8tb02938e

168. Zeng QY, Han Y, Li HY, et al. Design of thermosensitive bioglass/agarose-alginate composite hydrogel for chronic wound healing. *J Mater Chem B*. 2015;3:8856–8864. doi:10.1039/c5tb01758k
169. Jiang YQ, Han YM, Wang J, et al. Space-oriented nanofibrous scaffold with silicon-doped amorphous calcium phosphate nano-coating for diabetic wound healing. *ACS Appl Bio Mater*. 2019;2:787–795. doi:10.1021/acsabm.8b00657
170. Nunan R, Harding KG, Martin P. Clinical challenges of chronic wounds: searching for an optimal animal model to recapitulate their complexity. *Dis Model Mech*. 2014;7:1205–1213. doi:10.1242/dmm.016782
171. Sen CK. Wound healing essentials: let there be oxygen. *Wound Repair Regen*. 2009;17:1–18. doi:10.1111/j.1524-475X.2008.00436.x
172. Giacco F, Brownlee M. Oxidative stress and diabetic complications. *Circ Res*. 2010;107:1058–1070. doi:10.1161/CIRCRESAHA.110.223545
173. Lan CCE, Wu CS, Huang SM, et al. High-glucose environment enhanced oxidative stress and increased interleukin-8 secretion from keratinocytes: new insights into impaired diabetic wound healing. *Diabetes*. 2013;62:2530–2538. doi:10.2337/db12-1714
174. Zhu Y, Cankova Z, Iwanaszko M, et al. Potent laminin-inspired antioxidant regenerative dressing accelerates wound healing in diabetes. *Proc Natl Acad Sci*. 2018;115(26):6816–6821. doi:10.1073/pnas.1804262115
175. Ahmed R, Tariq M, Ali I, et al. Novel electrospun chitosan/poly-vinylalcohol/zinc oxide nanofibrous mats with antibacterial and antioxidant properties for diabetic wound healing. *Int J Biol Macromol*. 2018;120:385–393. doi:10.1016/j.ijbiomac.2018.08.057
176. Nureddin A, Ali DM, Seda KN, et al. Advances in controlled oxygen generating biomaterials for tissue engineering and regenerative therapy. *Biomaterials*. 2020;21(1):56–72. doi:10.1021/acs.biomac.9b00546
177. Eileen P, Coronel MM, Fraker CA, et al. Preventing hypoxia-induced cell death in beta cells and islets via hydrolytically activated, oxygen-generating biomaterials. *Proc Natl Acad Sci*. 2012;109(11):4245–4250. doi:10.1073/pnas.1113560109
178. Harrison BS, Eberli D, Lee SJ, et al. Oxygen producing biomaterials for tissue regeneration. *Biomaterials*. 2007;28:4628–4634. doi:10.1016/j.biomaterials.2007.07.003
179. Abdi SIH, Ng SM, Lim JO. An enzyme-modulated oxygen-producing micro-system for regenerative therapeutics. *Int J Pharm*. 2011;409:203–205. doi:10.1016/j.ijpharm.2011.02.041
180. White JC, Stoppel WL, Susan C, et al. Addition of perfluorocarbons to alginate hydrogels significantly impacts molecular transport and fracture stress. *J Biomed Mater Res A*. 2013;101(2):438–446. doi:10.1002/jbm.a.34344
181. Shiekh PA, Singh A, Kumar A. Exosome laden oxygen releasing antioxidant and antibacterial cryogel wound dressing OxOBand alleviate diabetic and infectious wound healing. *Biomaterials*. 2020;249:120020. doi:10.1016/j.biomaterials.2020.120020
182. Kim HJ, Matsuda H, Zhou H, et al. Ultrasound-triggered smart drug release from a poly (dimethylsiloxane)–mesoporous silica composite. *Adv Mater*. 2006;18(23):3083–3088. doi:10.1002/adma.200600387
183. Song X, Feng L, Liang C, et al. Ultrasound triggered tumor oxygenation with oxygen-shuttle nanoperfluorocarbon to overcome hypoxia-associated resistance in cancer therapies. *Nano Lett*. 2016;16(10):6145–6153. doi:10.1021/acs.nanolett.6b02365
184. Song G, Liang C, Yi X, et al. Cancer therapy: perfluorocarbon-loaded hollow Bi₂Se₃ nanoparticles for timely supply of oxygen under near-infrared light to enhance the radiotherapy of cancer. *Adv Mater*. 2016;28(14):2654. doi:10.1002/adma.201504617
185. Castro CI, Briceno JC. Perfluorocarbon-based oxygen carriers: review of products and trials. *Artif Organs*. 2010;34(8):622–634. doi:10.1111/j.1525-1594.2009.00944.x
186. Wang W, Cheng Y, Yu P, et al. Perfluorocarbon regulates the intratumoural environment to enhance hypoxia-based agent efficacy. *Nat Commun*. 2019;10(1):1580. doi:10.1038/s41467-019-09389-2
187. Marano F, Argenziano M, Frairia R, et al. Doxorubicin-loaded nanobubbles combined with extracorporeal shock waves: basis for a new drug delivery tool in anaplastic thyroid cancer. *Thyroid*. 2016;26(5):705–716. doi:10.1089/thy.2015.0342
188. Marano F, Frairia R, Rinella L, et al. Combining doxorubicin-nanobubbles and shockwaves for anaplastic thyroid cancer treatment: preclinical study in a xenograft mouse model. *Endocr Relat Cancer*. 2017;24(6):275–286. doi:10.1530/ERC-17-0045
189. Wang S, Yin C, Han X, et al. Improved healing of diabetic foot ulcer upon oxygenation therapeutics through oxygen-loading nano-perfluorocarbon triggered by radial extracorporeal shock wave. *Oxid Med Cell Longev*. 2019;2019:5738368. doi:10.1155/2019/5738368
190. Zehra M, Zubairi W, Hasan A, et al. Oxygen generating polymeric nano fibers that stimulate angiogenesis and show efficient wound healing in a diabetic wound model. *Int J Nanomedicine*. 2020;15:3511–3522. doi:10.2147/IJN.S248911
191. Zhang XX, Chen GP, Liu YX, et al. Black phosphorus-loaded separable microneedles as responsive oxygen delivery carriers for wound healing. *ACS Nano*. 2020;14:5901–5908. doi:10.1021/acsnano.0c01059
192. Abudula T, Gauthaman K, Hammad AH, et al. Oxygen-releasing antibacterial nanofibrous scaffolds for tissue engineering applications. *Polymers*. 2020;12:1233. doi:10.3390/polym12061233
193. Kang JI, Park KM, Park KD. Oxygen-generating alginate hydrogels as a bioactive acellular matrix for facilitating wound healing. *J Ind Eng Chem*. 2019;69:397–404. doi:10.1016/j.jiec.2018.09.048
194. Zhang T, Han ZY, Zhang W, et al. Cyanoacrylate-encapsulated calcium peroxide achieved oxygen-sustained release and promoted wound healing. *Int J Polym Mater Poly Biomater*. 2020;69:703–708. doi:10.1080/00914037.2019.1600518
195. Durante W. Hydrogen sulfide therapy in diabetes-accelerated atherosclerosis: awhiff of success. *Diabetes*. 2016;65:2832–2834. doi:10.2337/dbi16-0042
196. Coletta C, Papapetropoulos A, Erdelyi K, et al. Hydrogen sulfide and nitric oxide are mutually dependent in the regulation of angiogenesis and endothelium-dependent vasorelaxation. *PNAS*. 2012;109:9161–9166. doi:10.1073/pnas.1202916109
197. Lin WC, Huang CC, Lina SJ, et al. In situ depot comprising phase-change materials that can sustainably release a gasotransmitter H₂S to treat diabetic wounds. *Biomaterials*. 2017;145:1–8. doi:10.1016/j.biomaterials.2017.08.023
198. Hamdan S, Pastar I, Drakulich S, et al. Nanotechnology-driven therapeutic interventions in wound healing: potential uses and applications. *ACS Central Science*. 2017;3:163–175. doi:10.1021/acscentsci.6b00371
199. Zhao YZ, Vanhoutte PM, Leung SWS. Vascular nitric oxide: beyond eNOS. *J Pharmacol Sci*. 2015;129:83–94. doi:10.1016/j.jphs.2015.09.002
200. Balakumar P, Chakkarwar VA, Krishan P, et al. Vascular endothelial dysfunction: a tug of war in diabetic nephropathy? *Biomed Pharmacother*. 2009;63:171–179. doi:10.1016/j.biopha.2008.08.008
201. Chen YJ, Wu SC, Wang HC, et al. Activation of angiogenesis and wound healing in diabetic mice using NO-delivery dinitrosyl iron complexes. *Mol Pharmaceutics*. 2019;16:4241–4251. doi:10.1021/acs.molpharmaceut.9b00586
202. Horikoshi S, Serpone N. Introduction to nanoparticles. *Micro-Waves Nanoparticle Synth Fundam Appl*. 2013;1–24. doi:10.1002/9783527648122.ch1
203. Pantarotto D, Partidos CD, Hoebeke J, et al. Immunization with peptide-functionalized carbon nanotubes enhances virus-specific neutralizing antibody responses. *Chem Biol*. 2016;10(10):961–966. doi:10.1016/j.chembiol.2003.09.011

204. Salata O. Applications of nanoparticles in biology and medicine. *J Nanobiotechnology*. 2004;2(1):3. doi:10.1186/1477-3155-2-3
205. Bruchez Jr. JM. Semiconductor nanocrystals as fluorescent biological labels. *Science*. 1998;281(5385):2013–2016. doi:10.1126/science.281.5385.2013
206. Wang S, Mamedova N, Kotov NA, et al. Antigen/antibody immunocomplex from CdTe nanoparticle bioconjugates. *Nano Lett*. 2002;2(8):817–822. doi:10.1021/nl0255193
207. Tong Z, Dong L, Zhou L, et al. Nisin inhibits dental caries-associated microorganism in vitro. *Peptides*. 2010;31:2003–2008. doi:10.1021/acsbiomaterials.9b00547
208. He X, Ding YF, Xie WJ, et al. Rubidium-containing calcium alginate hydrogel for antibacterial and diabetic skin wound healing applications. *ACS Biomater Sci Eng*. 2019;5:4726–4738. doi:10.1021/acsbiomaterials.9b00547
209. Kumar S, Lakshmanan VK, Raj M, et al. Evaluation of wound healing potential of β -chitin hydrogel/nano zinc oxide composite bandage. *Pharm Res*. 2013;30:523–537. doi:10.1007/s11095-012-0898-y
210. Augustine R, Hasan A, Patan NK, et al. Cerium oxide nanoparticle incorporated electrospun poly(3-hydroxybutyrate-co-3-hydroxyvalerate) membranes for diabetic wound healing applications. *ACS Biomater Sci Eng*. 2020;6:58–70. doi:10.1021/acsbiomaterials.8b01352
211. Soenen SJ, Paak WJ, Rejman J, et al. (Inter)Cellular stability of inorganic nanoparticles: effects on cytotoxicity, particle functionality, and biomedical applications. *Chem Rev*. 2015;115:2109–2135. doi:10.1021/cr400714j
212. Gao Q, Zhang X, Yin WY, et al. Functionalized MoS₂ nanovehicle with near-infrared laser-mediated nitric oxide release and photothermal activities for advanced bacteria-infected wound therapy. *Small*. 2018;14(45):1802290. doi:10.1002/sml.201802290
213. Zhao Y, Cai Q, Qi W, et al. BSA-CuS nanoparticles for photothermal therapy of diabetic wound infection in vivo. *Biol Chem Chem Biol*. 2018;3:9510–9516. doi:10.1002/slct.201802069
214. Thangavel P, Kannan R, Ramachandran B, et al. Development of reduced graphene oxide (rGO)-isabgol nanocomposite dressings for enhanced vascularization and accelerated wound healing in normal and diabetic rats. *J Colloid Interface Sci*. 2018;517:251–264. doi:10.1016/j.jcis.2018.01.110
215. Sun L, Zhang Y, Wang Y, et al. Real-time subcellular imaging based on graphene biosensors. *Nanoscale*. 2018;10(4):1759–1765. doi:10.1039/c7nr04749d
216. Jing X, Mi HY, Napiwocki BN, et al. Mussel-inspired electroactive chitosan/graphene oxide composite hydrogel with rapid self-healing and recovery behavior for tissue engineering. *Carbon*. 2017;125:557–570. doi:10.1016/j.carbon.2017.09.071
217. Tessmar JK, Göpferich AM. Matrices and scaffolds for protein delivery in tissue engineering. *Adv Drug Delivery Rev*. 2007;59:274. doi:10.1016/j.addr.2007.03.020
218. Andrew JS, Anglin EJ, Wu EC, et al. Sustained release of a monoclonal antibody from electrochemically prepared mesoporous silicon oxide. *Adv Funct Mater*. 2011;20:4168. doi:10.1002/adfm.201190106
219. Rytönen J, Arukuusk P, Xu W, et al. Porous silicon-cell penetrating peptide hybrid nanocarrier for intracellular delivery of oligonucleotides. *Mol Pharmaceutics*. 2014;11:382–390. doi:10.1021/mp4002624
220. Christopher TT, Steven JPM, Elizabeth M, et al. Delivery of flightless I neutralizing antibody from porous silicon nanoparticles improves wound healing in diabetic mice. *Adv Healthcare Mater*. 2017;6:1600707. doi:10.1002/adhm.201600707
221. Xie Z, Paras CB, Weng H, et al. Dual growth factor releasing multi-functional nanofibers for wound healing. *Acta Biomater*. 2013;9(12):9351–9359. doi:10.1016/j.actbio.2013.07.030
222. Majd SA, Khorasani MR, Moshtaghian SJ, et al. Application of chitosan/PVA nano fiber as a potential wound dressing for streptozotocin-induced diabetic rats. *Int J Biol Macromol*. 2016;92:1162–1168. doi:10.1016/j.ijbiomac.2016.06.035
223. Xia GX, Liu Y, Tian MP, et al. Nanoparticles/thermosensitive hydrogel reinforced with chitin whiskers as wound dressing for treating chronic wounds. *J Mater Chem B*. 2017;5:3172–3185. doi:10.1039/c7tb00479f
224. Correa VLR, Martins JA, Souza TR, et al. Melatonin loaded lecithin-chitosan nanoparticles improved the wound healing in diabetic rats. *Int J Biol Macromol*. 2020;162:1465–1475. doi:10.1016/j.ijbiomac.2020.08.027
225. Patrulea V, Ostafe V, Borchard G, et al. Chitosan as a starting material for wound healing applications. *Eur J Pharm Biopharm*. 2015;97:417–426. doi:10.1016/j.ejpb.2015.08.004
226. Ali L, Ahmad M, Aamir MN, et al. Venlafaxine-loaded sustained-release poly (hydroxyethyl methacrylate-co-itaconic acid) hydrogel composites: their synthesis and in vitro/in vivo attributes. *Iran Polym J*. 2019;1–8. doi:10.1007/s13726-019-00697-4
227. Paterson SM, Shadforth AMA, Brown DH, et al. The synthesis and degradation of collagenase-degradable poly(2-hydroxyethyl methacrylate)-based hydrogels and sponges for potential applications as scaffolds in tissue engineering. *Mater Sci Eng C Mater Biol Appl*. 2012;32(8):2536–2544. doi:10.1016/j.msec.2012.07.037
228. Lin YS, Ming LJ, Peng JS, et al. Radical annihilation of γ -ray-irradiated contact lens blanks made of a 2-hydroxyethyl methacrylate copolymer at elevated temperatures. *J Appl Polym Sci*. 2010;117(6):3114–3120. doi:10.1002/app.31947
229. Shah SA, Sohail M, Minhas MU, et al. pH-responsive CAP-co-poly (methacrylic acid)-based hydrogel as an efficient platform for controlled gastrointestinal delivery: fabrication, characterization, in vitro and in vivo toxicity evaluation. *Drug Deliv Transl Res*. 2019;9(2):555–577. doi:10.1007/s13346-018-0486-8
230. Yu L, Ding J. Injectable hydrogels as unique biomedical materials. *Chem Soc Rev*. 2008;37:1473–1481. doi:10.1039/b713009k
231. Zheng ZQ, Bian SQ, Li ZQ, et al. Catechol modified quaternized chitosan enhanced wet adhesive and antibacterial properties of injectable thermo-sensitive hydrogel for wound healing. *Carbohydr Polym*. 2020;249:116826. doi:10.1016/j.carbpol.2020.116826
232. Cai L, Dewi RE, Heilshorn SC. Injectable hydrogels with in situ double network formation enhance retention of transplanted stem cells. *Adv Funct Mater*. 2015;25:1344–1351. doi:10.1002/adfm.201403631
233. Truong VX, Ablett MP, Richardson SM, et al. Simultaneous orthogonal dual-click approach to tough, in-situ-forming hydrogels for cell encapsulation. *J Am Chem Soc*. 2015;137:1618–1622. doi:10.1021/ja511681s
234. Yang JA, Yeom J, Hwang BW, et al. In situ-forming injectable hydrogels for regenerative medicine. *Prog Polym Sci*. 2014;39:1973–1986. doi:10.1016/j.progpolymsci.2014.07.006
235. Eggermont LJ, Rogers ZJ, Colombani T, et al. Injectable cryogels for biomedical applications. *Trends Biotechnol*. 2020;38:418–431. doi:10.1016/j.tibtech.2019.09.008
236. Chen H, Cheng RY, Zhao X, et al. An injectable self-healing coordinative hydrogel with antibacterial and angiogenic properties for diabetic skin wound repair. *NPG Asia Mater*. 2019;11:3. doi:10.1038/s41427-018-0103-9
237. Wang SQ, Zheng H, Zhou L, et al. Nanoenzyme-reinforced injectable hydrogel for healing diabetic wounds infected with multidrug resistant bacteria. *Nano Lett*. 2020;20:5149–5158. doi:10.1021/acs.nanolett.0c01371
238. Li J, Hu WQ, Zhang YJ, et al. pH and glucose dually responsive injectable hydrogel prepared by in situ crosslinking of phenylboronic modified chitosan and oxidized dextran. *J Polym Sci Part A: Polym Chem*. 2015;53:1235–1244. doi:10.1002/pola.27556

239. Zhu YN, Zhang JM, Song JY, et al. A multifunctional pro-healing zwitterionic hydrogel for simultaneous optical monitoring of pH and glucose in diabetic wound treatment. *Adv Funct Mater.* 2019;1905493. doi:10.1002/adfm.201905493
240. Liu Y, Pharr M, Salvatore GA. Lab-on-skin: a review of flexible and stretchable electronics for wearable health monitoring. *ACS Nano.* 2017;11:9614–9635. doi:10.1021/acsnano.7b04898
241. Liang S, Zhang Y, Wang H, et al. Paintable and rapidly bondable conductive hydrogels as therapeutic cardiac patches. *Adv Mater.* 2018;30:1704235. doi:10.1002/adma.201704235
242. Liao M, Wan P, Wen J, et al. Wearable, healable, and adhesive epidermal sensors assembled from mussel-inspired conductive hybrid hydrogel framework. *Adv Funct Mater.* 2017;27:1703852. doi:10.1002/adfm.201703852
243. Zhou Y, Wan CJ, Yang YS, et al. Highly stretchable, elastic, and ionic conductive hydrogel for artificial soft electronics. *Adv Funct Mater.* 2019;29:1806220. doi:10.1002/adfm.201806220
244. Hua DW, Gao ST, Zhang MJ, et al. A novel xanthan gum-based conductive hydrogel with excellent mechanical, biocompatible, and self-healing performances. *Carbohydr Polym.* 2020;247:116743. doi:10.1016/j.carbpol.2020.116743
245. Zhang JJ, Wu C, Xu YY, et al. A highly stretchable and conductive self-healing hydrogel for temperature and strain sensing and chronic wound treatment. *ACS Appl Mater Interfaces.* 2020;12:40990–40999. doi:10.1021/acsami.0c08291
246. Zhao H, Huang J, Li Y, et al. ROS-scavenging hydrogel to promote healing of bacteria infected diabetic wounds. *Biomaterials.* 2020;258:120286. doi:10.1016/j.biomaterials.2020.120286
247. Ma HS, Zhou Q, Chang J, et al. Grape seed-inspired smart hydrogel scaffolds for melanoma therapy and wound healing. *ACS Nano.* 2019;13:4302–4311. doi:10.1021/acsnano.8b09496
248. Wan WB, Cai F, Huang JY, et al. A skin-inspired 3D bilayer scaffold enhances granulation tissue formation and anti-infection for diabetic wound healing. *J Mater Chem B.* 2019;7:2954–2961. doi:10.1039/c8tb03341b
249. Chen SX, Wang HJ, Su YJ, et al. Mesenchymal stem cell-laden, personalized 3D scaffolds with controlled structure and fiber alignment promote diabetic wound healing. *Acta Biomater.* 2020;108:153–167. doi:10.1016/j.actbio.2020.03.035
250. Yu BR, He CH, Wang WB, et al. Asymmetric wettable composite wound dressing prepared by electrospinning with bioinspired micropatterning enhances diabetic wound healing. *ACS Appl Bio Mater.* 2020;3:5383–5394. doi:10.1021/acsbm.0c00695
251. Bao F, Pei G, Wu ZC, et al. Bioactive self-pumping composite wound dressings with micropore array modified janus membrane for enhanced diabetic wound healing. *Adv Funct Mater.* 2020;2005422. doi:10.1002/adfm.202005422
252. Huang JL, Zhou JF, Zhuang JY, et al. Strong near-infrared absorbing and biocompatible CuS nanoparticles for rapid and efficient photothermal ablation of gram-positive and -negative bacteria. *ACS Appl Mater Interfaces.* 2017;9:36606–36614. doi:10.1021/acsami.7b11062
253. Chen J, Cheng G, Liu R, et al. Enhanced physical and biological properties of silk fibroin nanofibers by layer-by-layer deposition of chitosan and rectorite. *J Colloid Interface Sci.* 2018;523:208–216. doi:10.1016/j.jcis.2018.03.093
254. Tang ZY, Wang Y, Podsiadlo P, et al. Biomedical applications of layer-by-layer assembly: from biomimetics to tissue engineering. *Adv Mater.* 2006;18:3203. doi:10.1002/adma.200790025
255. Shi YH, Wan DJ, Huang JH, et al. Stable LBL self-assembly coating porous membrane with 3D heterostructure for enhanced water treatment under visible light irradiation. *Chemosphere.* 2020;252:126581. doi:10.1016/j.chemosphere.2020.126581
256. Wu G, Ma X, Fan L, et al. Accelerating dermal wound healing and mitigating excessive scar formation using LBL modified nanofibrous mats. *Mater Des.* 2020;185:108265. doi:10.1016/j.matdes.2019.108265
257. Oroojalian F, Jahanafrooz Z, Chogan F, et al. Synthesis and evaluation of injectable thermosensitive penta-block copolymer hydrogel (PNIPAAm-PCL-PEG-PCL-PNIPAAm) and star-shaped poly(CLCOLA)-b-PEG for wound healing applications. *J Cell Biochem.* 2019;120(10):17194–17207. doi:10.1002/jcb.28980
258. Andrade TAM, Iyer A, Das PK, et al. The inflammatory stimulus of a natural latex biomembrane improves healing in mice. *Braz J Med Biol Res.* 2011;44(10):1036–1047. doi:10.1590/S0100-879X2011007500116
259. de Barros NR, Miranda MCR, Borges FA, et al. Oxytocin sustained release using natural rubber latex membranes. *Int J Pept Res Ther.* 2016;22(4):435–444. doi:10.1007/s10989-016-9523-y
260. Davi CP, Lombello CB, Ferreira M. Higher cellular interaction and faster production of natural rubber latex LbL films by spraying method. *Int J Adv Manuf Tech.* 2019;100:999–1005. doi:10.1007/s00170-018-2778-z
261. Long J, Etxeberria AE, Nand AV, et al. A 3D printed chitosan-pectin hydrogel wound dressing for lidocaine hydrochloride delivery. *Mater Sci Eng C.* 2019;104:109873. doi:10.1016/j.msec.2019.109873
262. İlhan E, Cesur S, Güler E, et al. Development of *Satureja cuneifolia*-loaded sodium alginate/polyethylene glycol scaffolds produced by 3D-printing technology as a diabetic wound dressing material. *Int J Biol Macromol.* 2020;161:1040–1054. doi:10.1016/j.ijbiomac.2020.06.086
263. Wu MX, Zhang YJ, Huang H, et al. Assisted 3D printing of microneedle patches for minimally invasive glucose control in diabetes. *Mater Sci Eng C.* 2020;117:111299. doi:10.1016/j.msec.2020.111299

International Journal of Nanomedicine

Publish your work in this journal

The International Journal of Nanomedicine is an international, peer-reviewed journal focusing on the application of nanotechnology in diagnostics, therapeutics, and drug delivery systems throughout the biomedical field. This journal is indexed on PubMed Central, MedLine, CAS, SciSearch®, Current Contents®/Clinical Medicine,

Submit your manuscript here: <https://www.dovepress.com/international-journal-of-nanomedicine-journal>

Dovepress

Journal Citation Reports/Science Edition, EMBase, Scopus and the Elsevier Bibliographic databases. The manuscript management system is completely online and includes a very quick and fair peer-review system, which is all easy to use. Visit <http://www.dovepress.com/testimonials.php> to read real quotes from published authors.