Cell sheet engineering: solvent effect on nanometric grafting of poly-N-isopropylacrylamide onto polystyrene substrate under ultraviolet radiation

Esmail Biazar¹

MT Khorasani²

M Daliri³

¹Department of Biomedical Engineering, Science and Research Branch, Islamic Azad University, Tehran, Iran; ²Biomaterial Department, Iran Polymer and Petrochemical Institute, Tehran, Iran; ³National Research Center for Genetic Engineering and Biotechnology, Tehran, Iran

Background: The best solvent type and ratio for grafting of poly-N-isopropylacrylamide (PNIPAAm) on the surface of polystyrene is obtained under ultraviolet radiation. In this study, the effects of solvents, such as water, methanol, and their combinations, under ultraviolet radiation were investigated successfully.

Method and results: Attenuated total reflection Fourier transform infrared analysis showed the existence of the graft PNIPAAm on the substrate for all samples resolved in solvents. The best solvent ratio and NIPAAm concentration for grafting was obtained with 40% NIPAAm concentrations resolved in a solvent of 9:1 (v/v) water/methanol (120%). Scanning electron microscopic and atomic force microscopic images clearly showed that a 10% increase of methanol to water would increase the amount of grafting. Surface topography and graft thickness in atomic force microscopic images of the grafted samples showed that the thickness of these grafts was about 600 nm. The drop water contact angles of the best grafted sample at 37°C and 4°C were 43.3° and 60.4°, respectively, which demonstrated the hydrophilicity and hydrophobicity of the grafted surfaces. Differential scanning calorimetric analysis also revealed the low critical solution temperature of the grafted sample to be 32°C. Thermoresponsive polymers were grafted to dishes covalently, which allowed epithelial cells to attach and proliferate at 37°C. The cells were also detached spontaneously without using enzymes when the temperature dropped below 4°C.

Conclusion: MTT analysis also showed good viability of cells on the grafted samples, suggesting that this type of grafted material had potential as a biomaterial for cell sheet engineering.

Keywords: nanometric grafting, solvent effect, poly-N-isopropylacrylamide, polystyrene film, ultraviolet radiation

Introduction

Poly-N-isopropylacrylamide (PNIPAAm) and its copolymers, due to high-speed transition from liquid to solid phase and a critical dissolution temperature of 32°C, can be used in the field of medical science, as well as in drug delivery systems and tissue engineering. At temperatures higher than 32°C, the material exists in a solid and hydrophobic state, and at temperatures below 32°C the polymer shows fully hydrated and hydrophilic properties. PNIPAAm was synthesized in 1957 by Wooten.¹ This smart polymer enables surface modification of materials for use in cell sheet engineering.^{2,5} Different methods for surface modification of polymers, eg, polyethylene, polypropylene, polystyrene, and polyethylene terephthalate, with PNIPAAm grafting using chemical and physical methods, including gamma-ray exposure, plasma, ozone, and ultraviolet and electron beam can be used, each with advantages and disadvantages.^{6,9}

Correspondence: Esmail Biazar
Science and Research Branch, Islamic Azad University, Tehran, Iran
Tel +98 911 718 0155
Fax +98 192 427 4411
Email kia_esm@yahoo.com

In all such methods, a radical is created on the surface and, during collision with a monomer, the polymerization process occurs.

The ultraviolet irradiation method, in terms of its simplicity and low cost, could potentially be a suitable method for biomaterial surface modification.^{10,11} Factors such as radiation distance, absorption intensity, wavelength used appropriately to the initiator, thickness, and usual factors, including degassing, substrate, initiators, and sensitizers, contributed to the ultraviolet radiation delivery.¹² Of course, this method is required for optical sensitizers or initiators such as anthraquinone¹³ or benzophenone.¹⁴ Selected solvents used in spectroscopy and polymerization with ultraviolet radiation are very important. Among the solvents used, water and ethanol are the most common organic solvents used in polymer chemistry. The hydrogen atoms of alcohols are transferred to radical substrates, and this can lead to competition between the monomers and alcohols with polymer radicals. One of the properties of alcohol as a solvent is constant chain transfer that is considered a very effective feature.¹⁵ In one study, the effect of solvents such as methanol, acetone, and water on 2-hydroxyethyl methacrylate polymerization under ultraviolet light on the nylon substrate was evaluated.¹⁵ The results showed that acetone, methanol, and water underwent the best grafting. The solvent effect may cause homopolymerization or grafting. Acetone, due to a lack of hydrogen, cannot donate a hydrogen atom to a substrate; hence, surface radicals can easily react with the monomer. However, there are problems with acetone, in particular, sensitivity to ultraviolet radiation (chromophore) and rapid evaporation during the process; thus, the amount of grafting is reduced.^{15–17} The negative effects of methanol as a solvent on acrylamide grafting to a polyethylene substrate¹⁸ have been investigated. Methanol caused swelling and lack of movement of hydrogen atoms. The constant chain transfer of water was zero, but the combination of water and methanol increased the grafting of acrylamide onto cellulose, and then decreased it.¹⁸ Methanol, due to its small molecular size, high swelling properties, and relatively low chain transfer constant (when its concentration in water was very low), showed more grafting than the heavier alcohols. When the concentration of methanol increased, the role of the chain transfer agent would be superior in the swelling process, and therefore grafting was reduced. Ethanol and propanol showed relatively reduced surface grafting due to weak swelling properties and a larger molecular size. The superiority of the stronger chain transfer agent with regard to swelling caused a sharp decrease in grafting. Alcohol solvents

could cause solvent evaporation due to their better solubility in the monomer under radiation, and this is important with long-term radiation. On the other hand, the use of water as a solvent was problematic due to lower solubility of acrylamides in water than in alcohols. Thus, a mixture of solvents could potentially solve these problems.^{15–19} In this study, several important solvents, including water, ethanol, and dimethyl sulfoxide and their complexes were used for grafting PNIPAAm onto a polystyrene surface by ultraviolet radiation. Finally, a nanometric uniform thickness was obtained. Also, the nanometric thickness of the grafting was shown to have an important effect in the process of adhesion and separation of cells and cell sheets. In this research, technical knowledge was also used to achieve intelligent surfaces with nanometric thicknesses using this type of radiation and the best solvent type and ratio for the polymerization process.

Methods and materials

Polystyrene dishes (Orange County Industrial Plastics, Anaheim, CA) with dimensions of 1 × 1 cm and 1 mm thickness, ethanol and methanol (Merck Co, Tehran, Iran), NIPAAm (Sigma-Aldrich, Tehran, Iran), n-hexane (Merck Co), distilled water, polystyrene, and epithelial cells (Pastor Institute, Tehran, Iran) were used in this study. The polystyrene dishes were put in the solution of ethanol-methanol in a 50/50 ratio for 24 hours to dissolve impurities and oils existing on the surface of the dishes. The dishes were then removed from the solution and washed in distilled water. For recrystallization of NIPAAm, 10.3 g of NIPAAm (Sigma-Aldrich) were dissolved in n-hexane 125 mL, and the solution was put in a refrigerator prior to grafting.

Sample preparation

The nonirradiated polystyrene samples were irradiated at a dose of 40 kGy (⁶⁰Co-γ-radiation source, supplied by Karaj Atomic Research Center, Karaj, Iran). The dose rate was 1 kGy/hour. Irradiation was carried out in air under ambient conditions. Monomers were dissolved in different percentages of solvents, including distilled water, ethanol, methanol, and acetone and their combinations, with a constant ratio of anthraquinone-2-sulfonic acid, and sodium salt monohydrate (3% w/v; Fluka Co, St. Louis, MO). The samples were degassed by nitrogen (2-bar mass flow rate) for 30 minutes. This process was used to increase the efficiency of free radical polymerization. The solutions were then poured in a plastic washer (diameter 1 cm and height 3 mm) attached to the polystyrene substrate. The samples in solution were exposed to an ultraviolet radiation source (black light,

160 W, 365 nm; Philips, Eindhoven, The Netherlands) for 30 minutes. Irradiation was carried out in air under ambient conditions. The samples were then removed and washed in distilled water, subsequently put in distilled water for 72 hours along with Soxhlet for removal of the ungrafted monomer, and then taken out for analysis. The effect of the solvents on the extent of grafting was measured using the following formula:

$$\text{grafting (\%)} = (w - w^{\circ}) 100 / w^{\circ}$$

where w and w° indicate the grafted and ungrafted sample weight, respectively.

Attenuated total reflection Fourier transform infrared

The samples were examined by attenuated total reflection Fourier transform infrared (ATR-FTIR; Nexus; Thermo Nicolet, Waltham, MA) before and after adjustment, and then were put under the instrument for investigation.

Surface morphology study

The surface characteristics of various modified and unmodified films were studied by scanning electron microscopy (Cambridge Stereoscan, Model S-360; Cambridge Scientific Instruments, Cambs, UK) to measure changes in surface morphology. The films were first coated with a layer of gold (Joel Fine Coat, ion sputter for two hours) to provide surface conduction before scanning. Surface topology characteristics and the thickness of various modified and unmodified films were studied by atomic force microscopy (TMX 2010 and the Nanosurf® EasyScan 2 model) to study changes in surface topology.

Contact angle analysis

The static contact angle of the sample surfaces was investigated using the contact angle measuring device (G10; Krüss, Hamburg, Germany) following the sessile drop method. The contact angle formed would be the angle between the solid/liquid and the liquid/steam joint surface. In order to review the sample surface's hydrophilic/hydrophobic behavior at high and low temperatures, a better sample was considered at two different temperatures of 4°C and 37°C, and the contact angles were measured at these temperatures.

Differential scanning calorimetry

Better samples were investigated by thermal analysis using a differential scanning calorimetry device (DSC 200 F3; Netzsch, Selb, Germany) at a heating rate of 5°C/min from 0°C to 60°C in a nitrogen gas atmosphere.

Biocompatibility study

Aliquots of cell suspension in RPMI medium including 300,000 SW742 epithelial cells were seeded on a 6-multiwell cell culture plate (Orange County Industrial Plastics) which was precoated with samples. The plate was put in an incubator (37°C, CO₂) over three hours for cell attachment, followed by rinsing of the loosely attached cells with phosphate buffer solution, and adding 2 mL of fresh medium to the cell culture in the incubator for seven days. Proliferation of cells was determined from measurement of viable cell numbers by MTT assay. The MTT tetrazolium compound was reduced by living cells into a colored formazan product that was soluble in tissue culture medium. The quantity of formazan product was directly proportional to the number of viable cells in the culture. The assays were performed by adding 1 mL of MTT solution (Sigma-Aldrich) and 9 mL of fresh medium to each well after aspirating the spent medium, and incubating at 37°C for four hours with protection from light. The colorimetric measurement of formazan dyeing was performed at a wavelength of 570 nm using a microplate reader (Rayto, Shenzhen, People's Republic of China).

For cell detachment, SW742 cells were seeded onto the samples at a density of 1,000,000 cells, and were cultured at 37°C under a humidified atmosphere of 5% CO₂. Cell detachment was evaluated by incubating the cultures at 4°C for up to 60 minutes. The culture medium containing the detached cells was transferred to a new well. The numbers of detached cells and cells attached to the original well were determined by MTT assay.

Results and discussion

Grafting percentages

The grafted polystyrene samples with the different solvents under ultraviolet radiation were weighed at a constant temperature. Table 1 and Figure 1A show that there was almost no grafting of samples using 100% solvents without water. More grafting is obtained with a methanol/water solvent of 10% (v/v). Table 2 and Figure 1B show an increase in grafting with increased NIPAAm concentration in a methanol/water solvent of 10% (v/v). The peaks around 20% (g/v) and 40% (g/v) were probably due to the

Table 1 Grafting percentage of polymer on surface according to solvents used

Solvent	Water	Methanol/ water 10%	Methanol/ water 25%	Methanol/ water 50%	Methanol 100%
Grafting (%)	45	55	42	20	7

Figure 1 **A)** Grafting percentage of N-isopropylacrylamide onto polystyrene with two different solvents and **B)** Effect of N-isopropylacrylamide concentration on grafting in 9:1 (v/v) water/methanol solvent.

Trommsdorff effect. The small peak around 20% might be attributed to water, while the large one around 40% would be attributable to methanol.

Attenuated total reflection Fourier transform infrared analysis

ATR-FTIR spectra results of the regular unadjusted and the ultraviolet radiation-adjusted polystyrene samples are shown in Figure 2. The NIPAAm grafted by the ultraviolet-radiated polystyrene ATR-FTIR spectra are shown in Figure 3. The PNIPAAm peak characteristics include 1601 cm^{-1} indicating -NH groups, $1730\text{--}1830\text{ cm}^{-1}$ indicating C=O groups, 3025 cm^{-1} indicating CH_3 groups, and 3443 cm^{-1} indicating -NH groups in PNIPAAm. All these peaks were found in PNIPAAm-grafted polystyrene samples. These observations show that grafting between the PNIPAAm and the polystyrene surface occurs by activation of ultraviolet radiation coating.

Surface morphology

The microscopic images for investigating the adjusted samples through ultraviolet radiation have been shown in Figures 3 and 4. These images show PNIPAAm grafting onto the preirradiated polystyrene for different solvents. Figure 3A is the atomic force microscopic image obtained from the preirradiated polystyrene samples. The surface topography and the graft thickness created on the

surfaces with different solvents are shown in the atomic force microscopic images. Figure 3B shows the surface topography for the grafted sample using the water solvent. Figure 3C shows the surface topography for the grafted sample in the solvent of 9:1 (v/v) water/methanol. Figure 3D is the atomic force microscopic image obtained from the grafted polystyrene samples in pure methanol. The mean graft thickness for the better sample grafting in the solvent of 9:1 (v/v) water/methanol and the pure water was about 600 nm, and the white spots indicate roughness created during radiation.

Figure 4 shows the surface topography and thickness of the grafted sample, with better grafting (120%) using the 40% NIPAAm concentration resolved in a solvent of 9:1 (v/v) water/methanol. The average graft thickness for this sample was about 2 μm , and the white spots indicated roughness created during radiation.

Figures 5A–D show the scanning electron microscopic images for the grafted polystyrene samples created using different solvents. The surface morphology clearly shows grafting and graft thickness on surfaces with different solvents. Figure 5A shows the surface morphology and thickness for the grafted sample in the water solvent. Figure 5B shows the surface morphology and thickness for the grafted sample in the solvent of 9:1 (v/v) water/methanol. Figure 5C shows the surface morphology and thickness for the grafted sample in the solvent of 9:1 (v/v) water/methanol with 40% of NIPAAm. The mean graft thickness for the better sample grafted in the solvent of 9:1 (v/v) water/methanol and with 40% of NIPAAm was about 600 nm and 2 μm . Figure 5D shows the surface morphology of the grafted sample in the solvent of 9:1 (v/v) water/methanol.

Table 2 Grafting percentage of polymer on surface according to N-isopropylacrylamide concentration

NIPAAm (%)	0	10	20	40	60
Grafting (%)	0	55	65	120	100

Abbreviation: NIPAAm, N-isopropylacrylamide.

Figure 2 Attenuated total reflection Fourier transform infrared spectra of the ungrafted polystyrene (bottom) and spectra of the grafted polystyrene by ultraviolet radiation (top).

Contact angle analysis

For contact angle measurement, the measured angle of normal polystyrene adjusted by ultraviolet-radiated PNIPAAm surface samples at 4°C and 37°C is shown in Table 3. The tabulated data for the best grafted sample (40% NIPAAm concentration resolved in the solvent of 9:1 (v/v) water/methanol)

indicate that the samples show different contact angles at 4°C and 37°C, which is another reason why PNIPAAm grafting onto a polystyrene surface occurs.

The average contact angles of 43.3° and 60.4° have been calculated for 4°C and 37°C temperatures, respectively. The results indicate a contact angle decrease below the

Figure 3 Atomic force microscopic image of grafted polystyrene under ultraviolet radiation (scale $1 \times 1 \mu\text{m}$). **A**) Preirradiated by gamma radiation (40 KGy), **B**) Grafted sample in water, **C**) Grafted sample in 9:1 (v/v) water/methanol solvent, **D**) Grafted sample in pure methanol solvent.

Figure 4 Atomic force microscopic image of grafted polystyrene with better grafting (120%) with 40% N-isopropylacrylamide concentration resolved in the solvent of 9:1 (v/v) water/methanol under ultraviolet radiation (scale $1 \times 1 \mu\text{m}$).

temperature of 32°C (4°C), as well as hydrophilic surface features. When the contact angle increased above 32°C temperature (37°C), the hydrophobic surface feature was also seen.

Differential scanning calorimetry

The samples were investigated by the differential scanning calorimetry device (Netzsch DSC 200 F3), with a heating rate of 5°C per minute from 0°C to 60°C in a nitrogen

Table 3 Contact angles for normal and preirradiated and grafted samples

	Normal	Grafted samples
Temperature ($^\circ\text{C}$)	$\theta_{\text{H}_2\text{O}}$	$\theta_{\text{H}_2\text{O}}$
25 Preirradiated (gamma ray)	90	$58.6 \pm 3.2^\circ$
37	90	$60.4 \pm 0.7^\circ$
4	90	$43.3 \pm 1.3^\circ$

gas atmosphere. Review of the differential scanning calorimetry data for the grafted samples showed a critical temperature for the grafted PNIPAAm using a water/methanol ratio of 9/1. Figure 6 shows the differential scanning calorimetry thermogram in which a slope curve is obtained at 32°C . This shows no significant change in smart polymer critical temperature during the radiation and grafting process.

Biocompatibility results

Biocompatibility data demonstrated that the grafted samples with better grafting (120%) with 40% of NIPAAm concentration resolved in the solvent of 9:1 (v/v) water/methanol under ultraviolet radiation supported epithelial cell adhesion and proliferation, and that the cells also maintained high viability (Figure 7). After culture for seven days on grafted samples, almost all cells were alive, suggesting that the grafted samples were suitable for cell attachment and proliferation, and that the viability was about 75% (Figure 7A). When the cells were placed outside the incubator and the medium was cooled from 37°C to 4°C , almost all of them were alive (Figure 7B) and the viability was as high as 70%.

Figure 8A shows good cell growth on the surface of grafted samples at the physiological temperature of 37°C . Figure 8B shows spontaneous cell growth detached from the grafted sample surface, in the absence of enzymes (trypsin/ethylenediamine tetra-acetic acid). Cell detachment efficiency from the grafted samples was high. In contrast, cell growth on the tissue culture polystyrene dishes did not show any temperature-dependent cell sheet detachment. After a longer period of cell cultivation (for seven days), confluent cells formed a continuous monolayer cell sheet on the surface of the grafted samples. The cell sheet was spontaneously detached from the surface of the thermoreversible grafted samples when cooled to 4°C without treating by any enzymes. As shown in Figure 8B, cell detachment started from the edge of the cell monolayer. After 60 minutes of incubation at 4°C , a monolayer cell sheet could be lifted up from the edge upon mild perturbation of the medium. A living cell sheet, completely detached from the culture surface, could be obtained within 60 minutes. Such results demonstrated

Figure 5 Scanning electron microscopy of grafted polystyrene under ultraviolet radiation. **A)** Grafted sample in water (cross section), **B)** Grafted sample in the solvent of 9:1 (v/v) water/methanol (cross section), **C)** Grafted sample in the solvent of 9:1 (v/v) water/methanol with 40% N-isopropylacrylamide (cross section), and **D)** Surface morphology of grafted sample.

Figure 6 Differential scanning calorimetry spectra of the grafted polystyrene with 40% N-isopropylacrylamide concentration resolved in the solvent of 9:1 (v/v) water/methanol under ultraviolet radiation.

Figure 7 Cell viability in grafted sample with 40% N-isopropylacrylamide concentration resolved in a solvent of 9:1 (v/v) water/methanol under ultraviolet radiation at physiological temperature (37°C, Figure 7A) and detached cells on the sample surface after 60 minutes of incubation at 4°C (Figure 7B) with cell viability on control tissue culture polystyrene dishes.

Figure 8 Epithelial cell growth on the grafted Petri dish at 37°C in Figure 5A, and in Figure 8B the cells detached spontaneously when temperature decreases below 4°C on the grafted sample is shown.

that cold treatment effectively released the cell sheet from the plate without damaging cell–cell connections.

Conclusion

The effect of solvents on polymer grafting in a polystyrene sample dish under ultraviolet radiation was studied. The ATR-FTIR spectrum showed formation of the grafted polymer on polystyrene surfaces. The chain transferring constant and molecular weight effect of solvents and their penetration into the materials led to competition between the solvents for grafting. The chain transfer constancy of water was nearly zero, but the monomer NIPAAm did not solve well. In contrast, the monomer was well solved in alcohol, but the chain transfer constancy increased with an increase in the molecular weight of the alcohol. Water combined with a low chain transfer constant and an alcohol of low molecular weight could be a good solvent for grafting. Imaging and gravimetric analysis of the grafting quantity with different solvents indicated an increase in the grafting quantity by adding 10% methanol to water with 40% of NIPAAm concentration. The scanning electron microscopic images showed the grafted surface morphology for different solvents, and we could clearly observe and compare our increases in graft increasing. The surface topology shown in the atomic force microscopic images confirmed these results. The graft thickness of the best samples of solvent in this study was about 600 nm. The contact angles 43° and 60° obtained at temperatures of 4°C and 37°C, as well as polymer critical temperature constancy (32°C) measured by the differential scanning calorimetry method indicated that grafting caused no change in PNIPAAm operation and function. Thermoresponsive polymers were grafted to the dishes covalently, which allowed epithelial cells to attach and proliferate at 37°C. Cells from the sheet also detached spontaneously when the temperature decreased below 32°C, without using enzymes. MTT analysis also showed good viability of the grafted samples. These characteristics suggest that these types of grafted materials have potential as biomaterials for cell sheet engineering.

Disclosure

The authors report no conflicts of interest in this work.

References

1. Heskins M, Guillet JE. Solution properties of poly(N-isopropylacrylamide). *J Macromol Sci Chem*. 1968;A28:1441–1455.
2. Da Silva RM, Mano JF, Reis RL. Smart thermoresponsive coatings and surfaces for tissue engineering: Switching cell-material boundaries. *Trends Biotechnol*. 2007;25:577–583.
3. Yakushiji T, Sakai K, Kikuchi A, Aoyagi T, Sakurai Y, Okano T. Graft architectural effects on thermo-responsive wettability changes of poly(N-isopropylacrylamide)-modified surfaces. *Langmuir*. 1998;14:4657–4662.
4. Kikuchi A, Okano T. Nanostructured designs of biomedical materials applications of cell sheet engineering to functional regenerative tissues and organs. *J Control Release*. 2005;101:69–84.
5. Galaev IY, Mattiasson B. Stimulus responsive surfaces: Possible implication for biochromatography, cell detachment and drug delivery. *Landes Bioscience*. 2003;6:116–129.
6. Biazar E, Zeinali R, Montazeri N, et al. Cell engineering: Nanometric grafting of poly-N-isopropylacrylamide onto polystyrene film by different doses of gamma radiation. *Int J Nanomedicine*. 2010;5:549–556.
7. Curti PS, De Moura MR, Radovanovic E, Rubira AF, Muniz EC. Surface modification of polystyrene and poly(ethylene terephthalate) by grafting poly(N-isopropylacrylamide). *J Mater Sci Mater Med*. 2002;13:1175–1180.
8. Joeng B, Gutowska A. Lessons from nature: Stimuli-responsive polymers and their applications. *Trends Biotechnol*. 2002;20:305–310.
9. Akiyama Y, Kikuchi A, Yamato M, Okano T. Ultrathin poly(N-isopropylacrylamide) grafted layer on poly(styrene) surfaces for cell adhesion/detachment control. *Langmuir*. 2004;20:5506–5511.
10. Delivopoulos E, Murray AF, Curtis JC. Effects of parylene-C photo-oxidation on serum-assisted glial and neuronal patterning. *J Biomed Mater Res A*. 2010;94:47–58.
11. Delivopoulos E, Murray AF, MacLeod NK, Curtis JC. Guided growth of neurons and glia using microfabricated patterns of parylene-C on a SiO₂ background. *Biomaterials*. 2009;30:2048–2058.
12. Deng J, Wang L, Liu L, Yang W. Developments and new applications of UV-induced surface graft polymerizations. *Prog Polym Sci*. 2009;34:156–193.
13. Geuskens G, Etoc A, Di Michele P. Surface modification of polymers VII: Photochemical grafting of acrylamide and N-isopropylacrylamide onto polyethylene initiated by anthraquinone-2-sulfonate adsorbed at the surface of the polymer. *Eur Polym J*. 2000;36:265–271.
14. Bousquet JA, Haidar B, Fouassier JP, Vidal A. Photocrosslinking of elastomer systems – III Ultraviolet light induced reactions in EPDM and EPR blended with or modified by grafting of derivatives of benzophenone. *Eur Polym J*. 1983;19:135–142.
15. Nandi US, Singh M. Chain transfer of alcohols in the polymerization of acrylic esters. *Makromolekulare Chemie*. 1982;183:1467–1472.
16. Sasaki T, Ratner BD, Hoffman AS. Radiation-induced co-graft polymerization of 2-hydroxyethyl methacrylate and ethyl methacrylate onto silicone rubber films. *Hydrogels for Medical and Related Applications, ACS Symposium Series*. 1976;3:283–294.
17. Lu J, Li J, Yi M, Ha H. Solvent effect on grafting polymerization of NIPAAm onto cotton cellulose via G-preirradiation method. *Radiat Phys Chem*. 2001;60:625–628.
18. Ogiwara Y, Takumi M, Kubota H. Photoinduced grafting of acrylamide onto polyethylene film by means of two-step method. *J Appl Polym Sci*. 1982;27:3743–3750.
19. Ranogajec F, Mlinac-Miak M. Improvement of the polymer stability by radiation grafting. *Radiat Phys Chem*. 2004;71:229–233.

International Journal of Nanomedicine

Publish your work in this journal

The International Journal of Nanomedicine is an international, peer-reviewed journal focusing on the application of nanotechnology in diagnostics, therapeutics, and drug delivery systems throughout the biomedical field. This journal is indexed on PubMed Central, MedLine, CAS, SciSearch®, Current Contents®/Clinical Medicine,

Submit your manuscript here: <http://www.dovepress.com/international-journal-of-nanomedicine-journal>

Dovepress

Journal Citation Reports/Science Edition, EMBASE, Scopus and the Elsevier Bibliographic databases. The manuscript management system is completely online and includes a very quick and fair peer-review system, which is all easy to use. Visit <http://www.dovepress.com/testimonials.php> to read real quotes from published authors.